

# SVENSK STANDARD

## SS-EN 14605:2005+A1:2009

Fastställt/Approved: 2009-05-25  
Publicerad/Published: 2009-08-18  
Utgåva/Edition: 1  
Språk/Language: engelska/English  
ICS: 13.340.10

---

**Skyddskläder mot kemikalier i vätskeform – Prestandakrav för skyddskläder mot kemikalier, med vätsketäta (Typ 3) eller stänktäta (Typ 4) anslutningar mellan olika delar av beklädnanden samt beklädnad begränsad till delar av kroppen (Typ PB (3) och PB (4))**

**Protective clothing against liquid chemicals – Performance requirements for clothing with liquid-tight (Type 3) or spray-tight (Type 4) connections, including items providing protection to parts of the body only (Types PB [3] and PB [4])**

This preview is downloaded from [www.sis.se](http://www.sis.se). Buy the entire standard via <https://www.sis.se/std-69817>

# Hitta rätt produkt och ett leveranssätt som passar dig

## Standarder

Genom att följa gällande standard både effektiviserar och säkrar du ditt arbete. Många standarder ingår dessutom ofta i paket.

## Tjänster

Abonnemang är tjänsten där vi uppdaterar dig med aktuella standarder när förändringar sker på dem du valt att abonnera på.

På så sätt är du säker på att du alltid arbetar efter rätt utgåva.

e-nav är vår online-tjänst som ger dig och dina kollegor tillgång till standarder ni valt att abonnera på dygnet runt. Med e-nav kan samma standard användas av flera personer samtidigt.

## Leveranssätt

Du väljer hur du vill ha dina standarder levererade. Vi kan erbjuda dig dem på papper och som pdf.

## Andra produkter

Vi har böcker som underlättar arbetet att följa en standard. Med våra böcker får du ökad förståelse för hur standarder ska följas och vilka fördelar den ger dig i ditt arbete. Vi tar fram många egna publikationer och fungerar även som återförsäljare. Det gör att du hos oss kan hitta över 500 unika titlar. Vi har även tekniska rapporter, specifikationer och "workshop agreement".

Matriser är en översikt på standarder och handböcker som bör läsas tillsammans. De finns på [sis.se](http://sis.se) och ger dig en bra bild över hur olika produkter hör ihop.

## Standardiseringsprojekt

Du kan påverka innehållet i framtida standarder genom att delta i någon av SIS ca 400 Tekniska Kommittéer.

# Find the right product and the type of delivery that suits you

## Standards

By complying with current standards, you can make your work more efficient and ensure reliability. Also, several of the standards are often supplied in packages.

## Services

Subscription is the service that keeps you up to date with current standards when changes occur in the ones you have chosen to subscribe to. This ensures that you are always working with the right edition.

e-nav is our online service that gives you and your colleagues access to the standards you subscribe to 24 hours a day. With e-nav, the same standards can be used by several people at once.

## Type of delivery

You choose how you want your standards delivered. We can supply them both on paper and as PDF files.

## Other products

We have books that facilitate standards compliance. They make it easier to understand how compliance works and how this benefits you in your operation. We produce many publications of our own, and also act as retailers. This means that we have more than 500 unique titles for you to choose from. We also have technical reports, specifications and workshop agreements.

Matrices, listed at [sis.se](http://sis.se), provide an overview of which publications belong together.

## Standardisation project

You can influence the content of future standards by taking part in one or other of SIS's 400 or so Technical Committees.

Europastandarden EN 14605:2005+A1:2009 gäller som svensk standard. Detta dokument innehåller den officiella engelska versionen av EN 14605:2005+A1:2009.

Denna standard ersätter SS-EN 14605:2005, utgåva 1.

The European Standard EN 14605:2005+A1:2009 has the status of a Swedish Standard. This document contains the official English version of EN 14605:2005+A1:2009.

This standard supersedes the Swedish Standard SS-EN 14605:2005, edition 1.

© Copyright/Upphovsrätten till denna produkt tillhör SIS, Swedish Standards Institute, Stockholm, Sverige. Användningen av denna produkt regleras av slutanvändarlicensen som återfinns i denna produkt, se standardens sista sidor.

© Copyright SIS, Swedish Standards Institute, Stockholm, Sweden. All rights reserved. The use of this product is governed by the end-user licence for this product. You will find the licence in the end of this document.

Upplysningar om sakinnehållet i standarden lämnas av SIS, Swedish Standards Institute, telefon 08-555 520 00.

Standarder kan beställas hos SIS Förlag AB som även lämnar allmänna upplysningar om svensk och utländsk standard.

Information about the content of the standard is available from the Swedish Standards Institute (SIS), tel +46 8 555 520 00.

Standards may be ordered from SIS Förlag AB, who can also provide general information about Swedish and foreign standards.

SIS Förlag AB, SE 118 80 Stockholm, Sweden. Tel: +46 8 555 523 10. Fax: +46 8 555 523 11.

E-mail: [sis.sales@sis.se](mailto:sis.sales@sis.se) Internet: [www.sis.se](http://www.sis.se)



EUROPEAN STANDARD  
NORME EUROPÉENNE  
EUROPÄISCHE NORM

**EN 14605:2005+A1**

May 2009

ICS 13.340.10

Supersedes EN 14605:2005

English Version

**Protective clothing against liquid chemicals - performance requirements for clothing with liquid-tight (Type 3) or spray-tight (Type 4) connections, including items providing protection to parts of the body only (Types PB [3] and PB [4])**

Vêtements de protection contre les produits chimiques liquides - Exigences relatives aux vêtements dont les éléments de liaison sont étanches au liquide (Type 3) ou aux pulvérisations (Type 4), y compris les articles d'habillement protégeant seulement certaines parties du corps (Types PB (3) et PB (4))

Schutzkleidung gegen flüssige Chemikalien - Leistungsanforderungen an Chemikalienschutzanzüge mit flüssigkeitsdichten (Typ 3) oder spraydichten (Typ 4) Verbindungen zwischen den Teilen der Kleidung, einschließlich der Kleidungsstücke, die nur einen Schutz für Teile des Körpers gewähren (Typen PB [3] und PB [4])

This European Standard was approved by CEN on 14 February 2005 and includes Amendment 1 approved by CEN on 5 April 2009.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the CEN Management Centre or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the CEN Management Centre has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Bulgaria, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland and United Kingdom.



EUROPEAN COMMITTEE FOR STANDARDIZATION  
COMITÉ EUROPÉEN DE NORMALISATION  
EUROPÄISCHES KOMITEE FÜR NORMUNG

**Management Centre: Avenue Marnix 17, B-1000 Brussels**

## Contents

	Page
Foreword.....	3
1 Scope .....	4
2 Normative references .....	4
3 Terms and definitions .....	5
4 Requirements .....	5
4.1 Materials .....	5
4.2 Seams, joins and assemblages.....	6
4.3 Performance requirements for whole suits (Types 3 and 4) .....	6
4.3.1 General.....	6
4.3.2 Pre-conditioning .....	6
4.3.3 Conditioning.....	7
4.3.4 Resistance to penetration by liquids.....	7
4.4 Visor .....	8
4.4.1 General.....	8
4.4.2 Mechanical strength of visor.....	8
4.4.3 Field of vision.....	8
4.4.4 Distortion of vision .....	8
5 Marking .....	8
6 Information supplied by the manufacturer .....	9
Annex ZA (informative) Relationship between this European Standard and the Essential Requirements of EU Directive 89/686/EEC.....	11
Bibliography .....	12

## Foreword

This document (EN 14605:2005+A1:2009) has been prepared by Technical Committee CEN/TC 162 “Protective clothing including hand and arm protection and lifejackets”, the secretariat of which is held by DIN.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by November 2009, and conflicting national standards shall be withdrawn at the latest by November 2009.

This document includes Amendment 1, approved by CEN on 2009-04-05.

This document supersedes A1 EN 14605:2005 A1.

The start and finish of text introduced or altered by amendment is indicated in the text by tags A1 A1.

This document has been prepared under a mandate given to CEN by the European Commission and the European Free Trade Association, and supports essential requirements of EU Directive 89/686/EEC.

For relationship with EU Directive(s), see informative Annex ZA, which is an integral part of this document.

This document includes a Bibliography.

According to the CEN/CENELEC Internal Regulations, the national standards organizations of the following countries are bound to implement this European Standard: Austria, Belgium, Bulgaria, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland and United Kingdom.

## 1 Scope

This document specifies the minimum requirements for the following types of limited use and reusable chemical protective clothing:

- Full-body protective clothing with liquid-tight connections between different parts of the clothing (Type 3: liquid-tight clothing) and, if applicable, with liquid-tight connections to component parts, such as hoods, gloves, boots, visors or respiratory protective equipment, which may be specified in other European Standards.  
Examples of such clothing are one-piece coveralls or two-piece suits, with or without hood or visors, with or without boot-socks or over-boots, with or without gloves;
- Full-body protective clothing with spray-tight connections between different parts of the clothing (Type 4: spray-tight clothing) and, if applicable, spray-tight connections to component parts, such as hoods, gloves, boots, visors or respiratory protective equipment, which may be specified in other European Standards.  
Examples of such clothing are one-piece coveralls or two-piece suits, with or without hood or visors, with or without boot-socks or over-boots, with or without gloves;
- Partial body protection garments offering protection to specific parts of the body against permeation of chemical liquids.  
Examples of such garments are e.g. laboratory coats, jackets, trousers, aprons, sleeves, hoods (not air-supplied) etc. As partial body protection leaves some parts of the body unprotected this document specifies only the performance requirements for the clothing material and the seams.

NOTE Partial body chemical protective garments which offer only protection against penetration of chemical liquids are within the scope of EN 13034 (Type PB [6] clothing).

## 2 Normative references

The following referenced documents are indispensable for the application of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

EN 340:2003, *Protective clothing — General requirements*

A1 *deleted text* A1

EN 12941:1998, *Respiratory protective devices - Powered filtering devices incorporating a helmet or a hood - Requirements, testing, marking*

A1 EN 14325:2004 A1, *Protective clothing against chemicals — Test methods and performance classification of chemical protective clothing materials, seams, joins and assemblages*

A1 *deleted text* A1

EN 31092, *Textiles — Determination of physiological properties — Measurement of thermal and water-vapour resistance under steady-state conditions (sweating guarded - hotplate test) (ISO 11092:1993)*

A1 EN ISO 3758, *Textiles – Care labelling code using symbols (ISO 3758:2005)* A1

CEN ISO/TR 11610:2004, *Protective clothing - Vocabulary (ISO/TR 11610:2004)*

A1 EN ISO 17491-3, *Protective clothing – Test methods for clothing providing protection against chemicals – Part 3: Determination of resistance to penetration by a jet of liquid (jet test) (ISO 17491-3:2008)* A1

A1 EN ISO 17491-4, *Protective clothing – Test methods for clothing providing protection against chemicals – Part 4: Determination of resistance to penetration by a spray of liquid (spray test) (ISO 17491-4:2008)* A1



ISO 7000, *Graphical symbols for use on equipment — Index and synopsis*

### 3 Terms and definitions

For the purposes of this document, the terms and definitions given in CEN ISO/TR 11610:2004 apply.

### 4 Requirements

#### 4.1 Materials

Chemical protective clothing materials shall be tested according to the requirements of Table 1 and in accordance with the test methods specified in EN 14325. A performance level of at least 1 shall be obtained for all requirements.

Chemical protective clothing materials shall not be known to cause skin irritation or have any adverse effect to health (see also EN 340:2003, 4.2).

Prior to testing, all chemical protective clothing materials shall be cleaned, if the manufacturer's instructions indicate that cleaning is allowed. Manufacturer's instructions with regard to number of cleaning cycles, cleaning procedures and possible reapplication of treatments shall be observed. If no maximum number of cleaning cycles is indicated, materials shall undergo five cycles.

All test specimens shall be conditioned at  $(20 \pm 2)$  °C and  $(65 \pm 5)$  % relative humidity for at least 24 h and testing shall start within 5 min after removing the specimen from the conditioning atmosphere.

**Table 1 — Test requirements for Type 3, Type 4, Type PB [3] and Type PB [4] clothing**

Clause in A1 EN 14325:2004 A1	Performance requirement
4.4	abrasion resistance
4.5	flex cracking resistance
4.6 <sup>a</sup>	flex cracking resistance at -30 °C
4.7	tear resistance (trapezoidal)
4.9	tensile strength
4.10	puncture resistance
4.11	resistance to permeation of liquids
A1 deleted text A1	
<sup>a</sup> Only applicable to clothing intended for use at very low temperatures.	

NOTE 1 Chemical protective clothing material, for which a test method in Table 1 does not provide a clear measurement end-point, should be marked "not applicable" in the test report and in the instructions for use. The reason why the test could not be completed should be indicated, e.g. where the elasticity of the specimen prevents to determine an end-point in the puncture resistance test.

NOTE 2 Materials should be as light and as flexible as possible in order to ensure wearer comfort as well as providing effective protection. Material properties are only one element for the determination of wearer comfort of protective clothing. Design features of the clothing may even have a more important influence on wearer comfort than material properties.

**NOTE 3** If resistance to heat and flame is required, the chemical protective clothing should be tested and marked according to the appropriate standard.

### 4.2 Seams, joins and assemblages

Seams, joins and assemblages shall be tested and classified according to the requirements of Table 2 and the corresponding clauses of EN 14325.

**Table 2 — Requirements for seams, joins and assemblages of Type 3, Type 4, Type PB [3]<sup>a</sup> and Type PB [4] clothing**

Performance requirement	Reference
resistance to permeation of liquids <sup>b</sup>	EN 14325:2004, 4.11
resistance to penetration by liquids <sup>c</sup>	EN ISO 17491-3 or EN ISO 17491-4
seam strength	EN 14325:2004, 5.5
<p><sup>a</sup> Seams, joins and assemblages of Type PB [3] clothing shall be tested to the jet test (EN ISO 17491-3).</p> <p><sup>b</sup> Applicable only to seams which are exposed in use. For partial body protection items only seams relevant to the construction shall be considered and a performance level of at least 1 shall be obtained.</p> <p><sup>c</sup> To be tested by whole suit tests, i.e. EN ISO 17491-3 (jet test) for Type 3 clothing and EN ISO 17491-4 (high level spray test) for Type 4 clothing.</p>	

### 4.3 Performance requirements for whole suits (Types 3 and 4)

#### 4.3.1 General

Chemical protective clothing shall fulfil the relevant requirements of EN 340. The clothing shall be made so that the wearer has freedom of movement and is as comfortable as possible, consistent with the protection afforded by the garment, as can be verified by the "seven movements" test, described in 4.3.4.1.

**NOTE 1** Wearer comfort can be judged in wear trials of the suit with test persons experienced in the type of work and environments for which the suits are intended as protective clothing.

Chemical protective clothing Type 3 and Type 4 shall fulfil the requirements specified in 4.3.4 (Table 3), when combined with additional protective equipment, i.e. for protection of hands, feet, face, head and/or respiratory tract, according to the manufacturer's instructions and when tested as a complete suit.

The requirements of this clause apply to the garment as a whole including component parts (e.g. gloves, boots, hoods or respirators) that are not integral to the garment. The joins and assemblages attaching these components are included within the scope of this document, whereas criteria for the components are given in other European Standards.

**NOTE 2** Partial body protection covers only specific areas of the body, leaving others exposed to the hazard. Because of this only limited testing of this type of clothing is appropriate and this product standard is defined accordingly.

#### 4.3.2 Pre-conditioning

Prior to testing, the chemical protective clothing shall be cleaned, if the manufacturer's instructions indicate that cleaning is allowed. Manufacturer's instructions with regard to number of cleaning cycles, cleaning procedures and possible reapplication of treatments shall be observed. If no maximum number of cleaning cycles is indicated, the clothing shall undergo five cleaning cycles.

### 4.3.3 Conditioning

All chemical protective clothing shall be conditioned for at least 24 h at the same conditions as used for the test.

### 4.3.4 Resistance to penetration by liquids

#### 4.3.4.1 General and preliminary testing

Type 3 chemical protective clothing shall be tested against penetration by liquids by means of a jet test in accordance with 4.3.4.3.

Type 4 chemical protective clothing shall be tested against penetration by liquids by means of a spray test in accordance with 4.3.4.2.

Partial body protection items Type PB [4] shall not be tested against these criteria. Seams, joins and assemblages of Type PB [3] clothing shall be tested to the jet test (EN ISO 17491-3 (A1)) (see also Table 2, footnote a)).

Prior to testing each suit in accordance with EN ISO 17491-3 (A1) or EN ISO 17491-4 (A1), a practical test shall be carried out by a human test subject. If more than one size of chemical protective suit is manufactured, the test subject will be asked to select the appropriate size according to the manufacturer's information leaflet. If applicable, the test subject shall also wear additional personal protective equipment, as specified in the manufacturer's instructions.

The test shall comprise three repetitions, at moderate speed, of the "seven movements" sequence described below.

Starting from a standing position in each case, carry out the following movement sequence:

- movement 1: kneel on both knees, lean forward and place both hands on the floor ( $45 \pm 5$ ) cm in front of the knees; crawl forward and backwards on hands and knees for a distance of three metres in each direction;
- movement 2: climb a vertical ladder at least four steps, rungs to be as encountered on a typical ladder;
- movement 3: position hands at chest level, palms out; reach directly overhead, interlock thumbs, extend arms fully upwards;
- movement 4: kneel on right knee, place left foot on floor with left knee bent ( $90 \pm 10$ ) °; touch thumb of right hand to toe of left shoe. Repeat movement with alternate posture, i.e. by kneeling on left knee and placing the right foot on the floor with knee bent at 90°;
- movement 5: extend arms fully in front of body, lock thumbs together, twist upper body ( $90 \pm 10$ ) ° left and right;
- movement 6: stand with feet shoulder width apart, arms at side; raise arms until they are parallel to the floor in front of the body; squat down as far as possible;
- movement 7: kneel as in movement 4, left arm hanging loosely at side; raise arm fully overhead. Repeat movement with alternate posture by alternating arms.

If the test subject is not able to perform one or several movements due to the hindrance of the suit or if the movements result in substantial damage to the suit, the suit shall be considered to have failed.

Suits equipped with a visor shall also pass the tests specified in 4.4 before further testing. Failure will result in a disqualification for further testing and the suit shall be considered to have failed.