

SVENSK STANDARD

SS-ISO 4666-1:2010

Fastställt/Approved: 2010-11-01
Publicerad/Published: 2010-12-21
Utgåva/Edition: 2
Språk/Language: engelska/English
ICS: 83.060

Vulkat gummi – Bestämning av temperaturstegring och beständighet mot utmattning vid flexometerprovning – Del 1: Grundprinciper (ISO 4666-1:2010, IDT)

Rubber, vulcanized – Determination of temperature rise and resistance to fatigue in flexometer testing – Part 1: Basic principles (ISO 4666-1:2010, IDT)

This preview is downloaded from www.sis.se. Buy the entire standard via <https://www.sis.se/std-75867>

Standarder får världen att fungera

SIS (Swedish Standards Institute) är en fristående ideell förening med medlemmar från både privat och offentlig sektor. Vi är en del av det europeiska och globala nätverk som utarbetar internationella standarder. Standarder är dokumenterad kunskap utvecklad av framstående aktörer inom industri, näringsliv och samhälle och befrämjar handel över gränser, bidrar till att processer och produkter blir säkrare samt effektiviserar din verksamhet.

Delta och påverka

Som medlem i SIS har du möjlighet att påverka framtida standarder inom ditt område på nationell, europeisk och global nivå. Du får samtidigt tillgång till tidig information om utvecklingen inom din bransch.

Ta del av det färdiga arbetet

Vi erbjuder våra kunder allt som rör standarder och deras tillämpning. Hos oss kan du köpa alla publikationer du behöver – allt från enskilda standarder, tekniska rapporter och standardpaket till handböcker och onlinetjänster. Genom vår webbtjänst e-nav får du tillgång till ett lättnavigerat bibliotek där alla standarder som är aktuella för ditt företag finns tillgängliga. Standarder och handböcker är källor till kunskap. Vi säljer dem.

Utveckla din kompetens och lyckas bättre i ditt arbete

Hos SIS kan du gå öppna eller företagsinterna utbildningar kring innehåll och tillämpning av standarder. Genom vår närhet till den internationella utvecklingen och ISO får du rätt kunskap i rätt tid, direkt från källan. Med vår kunskap om standarders möjligheter hjälper vi våra kunder att skapa verklig nytta och lönsamhet i sina verksamheter.

Vill du veta mer om SIS eller hur standarder kan effektivisera din verksamhet är du välkommen in på www.sis.se eller ta kontakt med oss på tel 08-555 523 00.



Standards make the world go round

SIS (Swedish Standards Institute) is an independent non-profit organisation with members from both the private and public sectors. We are part of the European and global network that draws up international standards. Standards consist of documented knowledge developed by prominent actors within the industry, business world and society. They promote cross-border trade, they help to make processes and products safer and they streamline your organisation.

Take part and have influence

As a member of SIS you will have the possibility to participate in standardization activities on national, European and global level. The membership in SIS will give you the opportunity to influence future standards and gain access to early stage information about developments within your field.

Get to know the finished work

We offer our customers everything in connection with standards and their application. You can purchase all the publications you need from us - everything from individual standards, technical reports and standard packages through to manuals and online services. Our web service e-nav gives you access to an easy-to-navigate library where all standards that are relevant to your company are available. Standards and manuals are sources of knowledge. We sell them.

Increase understanding and improve perception

With SIS you can undergo either shared or in-house training in the content and application of standards. Thanks to our proximity to international development and ISO you receive the right knowledge at the right time, direct from the source. With our knowledge about the potential of standards, we assist our customers in creating tangible benefit and profitability in their organisations.

If you want to know more about SIS, or how standards can streamline your organisation, please visit www.sis.se or contact us on phone +46 (0)8-555 523 00



Den internationella standarden ISO 4666-1:2010 gäller som svensk standard. Detta dokument innehåller den officiella engelska versionen av ISO 4666-1:2010.

Denna standard ersätter SS-ISO 4666-1, utgåva 1.

The International Standard ISO 4666-1:2010 has the status of a Swedish Standard. This document contains the official version of ISO 4666-1:2010.

This standard supersedes the Swedish Standard SS-ISO 4666-1, edition 1.

© Copyright/Upphovsrätten till denna produkt tillhör SIS, Swedish Standards Institute, Stockholm, Sverige. Användningen av denna produkt regleras av slutanvändarlicensen som återfinns i denna produkt, se standardens sista sidor.

© Copyright SIS, Swedish Standards Institute, Stockholm, Sweden. All rights reserved. The use of this product is governed by the end-user licence for this product. You will find the licence in the end of this document.

Uppllysningar om sakinnehållet i standarden lämnas av SIS, Swedish Standards Institute, telefon 08-555 520 00. Standarder kan beställas hos SIS Förlag AB som även lämnar allmänna uppllysningar om svensk och utländsk standard.

Information about the content of the standard is available from the Swedish Standards Institute (SIS), telephone +46 8 555 520 00. Standards may be ordered from SIS Förlag AB, who can also provide general information about Swedish and foreign standards.

Denna standard är framtagen av kommittén för Gummi och gummiprodukter, SIS/TK 154.

Har du synpunkter på innehållet i den här standarden, vill du delta i ett kommande revideringsarbete eller vara med och ta fram andra standarder inom området? Gå in på www.sis.se - där hittar du mer information.

Contents

Page

Foreword	iv
Introduction.....	v
1 Scope	1
2 Normative references	1
3 Terms and definitions	1
4 Test conditions	3
5 Test pieces	3
5.1 Form and dimensions	3
5.2 Preparation.....	3
5.3 Time interval between vulcanization and testing.....	4
5.4 Conditioning	4
5.5 Number	4
6 Apparatus	4
6.1 General	4
6.2 Temperature-controlled cabinet	4
6.3 Measurement of temperature	4
7 Procedure	5
7.1 General	5
7.2 Temperature of test.....	5
7.3 Measurement of temperature rise.....	5
7.4 Determination of fatigue life	5
7.5 Determination of limiting fatigue deformability and limiting fatigue stress.....	5
7.6 Determination of creep	6
7.7 Determination of set.....	6
8 Test report.....	6
Annex A (informative) Explanatory notes.....	7
Bibliography.....	9

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

International Standards are drafted in accordance with the rules given in the ISO/IEC Directives, Part 2.

The main task of technical committees is to prepare International Standards. Draft International Standards adopted by the technical committees are circulated to the member bodies for voting. Publication as an International Standard requires approval by at least 75 % of the member bodies casting a vote.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights.

ISO 4666-1 was prepared by Technical Committee ISO/TC 45, *Rubber and rubber products*, Subcommittee SC 2, *Testing and analysis*.

This second edition cancels and replaces the first edition (ISO 4666-1:1982), which has been technically revised.

ISO 4666 consists of the following parts, under the general title *Rubber, vulcanized — Determination of temperature rise and resistance to fatigue in flexometer testing*:

- *Part 1: Basic principles*
- *Part 2: Rotary flexometer*
- *Part 3: Compression flexometer (constant-strain type)*
- *Part 4: Constant-stress flexometer*

Introduction

All rubbers show viscoelastic behaviour. When subjected to cyclic deformation, they absorb a part of the deformation energy and convert this into heat. The heat generated leads to a temperature rise, which can be considerable in the interior of relatively thick components because of the low thermal conductivity of rubbers. In cases where the cyclic deformation is large or the temperature reaches high values, it is possible for damage to the rubber to occur through fatigue-initiated breakdown. The breakdown begins in the interior of the rubber, spreads outwards, and can finally lead to the complete breakdown of the component.

The tests specified in the various parts of this International Standard yield either temperature rise data or the fatigue life of the rubber under given test conditions. Measurement of fatigue life over a range of conditions can be used to determine the limiting fatigue deformability or limiting fatigue stress of the rubber. The instruments used, commonly called flexometers, subject test pieces to cycles of either constant-stress amplitude or constant-strain amplitude.

A distinction should be made between flexometer tests and fatigue tests conducted on thin test pieces undergoing tensile deformation or bending. In the fatigue tests, the temperature rise is generally negligible owing to the rapid dissipation of heat generated, and failure results from the initiation and growth of cracks which ultimately sever the test piece. ISO 132^[1] specifies tests for the determination of flex cracking and cut growth using the De Mattia-type machine. The determination of resistance to tension fatigue is specified in ISO 6943^[3].

Rubber, vulcanized — Determination of temperature rise and resistance to fatigue in flexometer testing —

Part 1: Basic principles

1 Scope

This part of ISO 4666 establishes general principles for flexometer testing and defines the terms used.

Flexometer testing makes possible predictions regarding the durability of rubbers in finished articles subject to dynamic flexing in service such as tyres, bearings, supports, V-belts, and cable-pulley insert rings. However, owing to the wide variations in service conditions, no simple correlation between the accelerated tests specified in the various parts of this International Standard and service performance can be assumed.

2 Normative references

The following referenced documents are indispensable for the application of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 4664-1:—¹⁾, *Rubber, vulcanized or thermoplastic — Determination of dynamic properties — Part 1: General guidance*

ISO 23529, *Rubber — General procedures for preparing and conditioning test pieces for physical test methods*

3 Terms and definitions

For the purposes of this document, the terms and definitions given in ISO 4664-1 and the following apply.

3.1

loading

subjection of the test piece to a predetermined stress or strain, either static or cyclic

3.2

pre-stress

σ_p

constant static stress to which the test piece is subjected during the test

NOTE 1 Pre-stress is expressed in pascals.

NOTE 2 Pre-stress can be used to simulate product requirements or simply to hold the test piece in the apparatus.

NOTE 3 The term “mean stress” (ISO 4664-1:—) is equivalent or near equivalent to “pre-stress”.

1) To be published. (Revision of ISO 4664-1:2005)

3.3

pre-strain

ε_p
constant static strain to which the test piece is subjected during the test

NOTE 1 Pre-strain can be used to simulate product requirements or simply to hold the test piece in the apparatus.

NOTE 2 The term “mean strain” (ISO 4664-1:—) is equivalent or near equivalent to “pre-strain”.

3.4

cyclic stress amplitude

σ_a
 τ_a
ratio of the force amplitude (cyclic force) superimposed upon the pre-strain or pre-stress to the appropriate cross-sectional area of the unstressed test piece

NOTE 1 Cyclic stress amplitude is expressed in pascals.

NOTE 2 The term “maximum stress amplitude” (ISO 4664-1:—) is equivalent or near equivalent to “cyclic stress amplitude”.

3.5

cyclic strain amplitude

ε_a
 γ_a
deformation amplitude (cyclic deformation) superimposed upon the pre-strain or pre-stress

NOTE 1 For certain flexometers, the cyclic strain is smaller than the pre-strain.

NOTE 2 In a compression flexometer, the pre-stress, σ_p , acts in the same direction as the cyclic strain amplitude, ε_a . In a rotary flexometer, a cyclic shear strain, γ_a , or cyclic shear stress, τ_a , acts at right angles to an axial compression pre-strain, ε_p , or axial compression pre-stress, σ_p .

NOTE 3 The term “maximum strain amplitude” (ISO 4664-1:—) is equivalent or near equivalent to “cyclic strain amplitude”.

3.6

heat generation

total heat generated in the test piece by energy absorption during the test

NOTE “Heat generation” should be distinguished from the deprecated, but sometimes used, expression “heat build-up”, which is normally associated with the temperature rise in the test piece.

3.7

temperature rise

increase in temperature of the test piece

NOTE The temperature rise is taken as the difference between the temperature measured at a given point in the test piece at a given time during the test and either the temperature at the beginning of the test or the ambient temperature.

3.8

fatigue breakdown

change in chemical structure, physical structure or composition of the test piece under the simultaneous action of stress and temperature

3.9

fatigue life

N
number of cycles required to produce failure or breakdown under a given static and cyclic loading

3.10

fatigue deformability

cyclic strain amplitude corresponding to a given fatigue life

3.11

fatigue stress

cyclic stress amplitude corresponding to a given fatigue life

3.12

limiting fatigue deformability

ε_{∞}

γ_{∞}

cyclic strain amplitude at which the fatigue life curve becomes essentially parallel to the log N axis

See Figure 1.

3.13

limiting fatigue stress

σ_{∞}

τ_{∞}

cyclic stress amplitude at which the fatigue life curve becomes essentially parallel to the log N axis

See Figure 1.

4 Test conditions

The relative ratings of rubbers having different moduli depend upon the type of loading used to evaluate them:

- a) σ_p and σ_a or τ_a constant;
- b) σ_p and ε_a or γ_a constant;
- c) ε_p and σ_a or τ_a constant;
- d) ε_p and ε_a or γ_a constant.

Both the type and magnitude of loading should be governed by the intended use of the rubber. In tests for heat generation, the magnitude should be high enough to generate a temperature rise that is sufficient to be discriminating, but not high enough to cause breakdown.

In tests for fatigue life, choose the loading that yields results capable of discriminating between materials.

NOTE It is also possible to conduct tests under constant-strain energy conditions.

5 Test pieces

5.1 Form and dimensions

Test pieces for flexometer testing shall be cylindrical. Dimensions differ according to the test method used.

5.2 Preparation

Test pieces shall be prepared and stored in accordance with ISO 23529. Test pieces may be prepared by vulcanization in moulds, or from slabs or finished parts by cutting, boring, and buffing. If test pieces are cut from a finished part, this shall be mentioned in the test report.