

SVENSK STANDARD

SS-ISO 4675:2018



Fastställt/Approved: 2018-07-03
Utgåva/Edition: 1
Språk/Language: engelska/English
ICS: 59.080.40

Gummi- eller plastbelagda tyger – Böjprovning vid låg temperatur (ISO 4675:2017, IDT)

Rubber- or plastics-coated fabrics – Low-temperature bend test (ISO 4675:2017, IDT)

This preview is downloaded from www.sis.se. Buy the entire standard via <https://www.sis.se/std-80005357>

Standarder får världen att fungera

SIS (Swedish Standards Institute) är en fristående ideell förening med medlemmar från både privat och offentlig sektor. Vi är en del av det europeiska och globala nätverk som utarbetar internationella standarder. Standarder är dokumenterad kunskap utvecklad av framstående aktörer inom industri, näringsliv och samhälle och befrämjar handel över gränser, bidrar till att processer och produkter blir säkrare samt effektiviserar din verksamhet.

Delta och påverka

Som medlem i SIS har du möjlighet att påverka framtida standarder inom ditt område på nationell, europeisk och global nivå. Du får samtidigt tillgång till tidig information om utvecklingen inom din bransch.

Ta del av det färdiga arbetet

Vi erbjuder våra kunder allt som rör standarder och deras tillämpning. Hos oss kan du köpa alla publikationer du behöver – allt från enskilda standarder, tekniska rapporter och standardpaket till handböcker och onlinetjänster. Genom vår webbtjänst e-nav får du tillgång till ett lättnavigerat bibliotek där alla standarder som är aktuella för ditt företag finns tillgängliga. Standarder och handböcker är källor till kunskap. Vi säljer dem.

Utveckla din kompetens och lyckas bättre i ditt arbete

Hos SIS kan du gå öppna eller företagsinterna utbildningar kring innehåll och tillämpning av standarder. Genom vår närhet till den internationella utvecklingen och ISO får du rätt kunskap i rätt tid, direkt från källan. Med vår kunskap om standarders möjligheter hjälper vi våra kunder att skapa verklig nytta och lönsamhet i sina verksamheter.

Vill du veta mer om SIS eller hur standarder kan effektivisera din verksamhet är du välkommen in på www.sis.se eller ta kontakt med oss på tel 08-555 523 00.



Standards make the world go round

SIS (Swedish Standards Institute) is an independent non-profit organisation with members from both the private and public sectors. We are part of the European and global network that draws up international standards. Standards consist of documented knowledge developed by prominent actors within the industry, business world and society. They promote cross-border trade, they help to make processes and products safer and they streamline your organisation.

Take part and have influence

As a member of SIS you will have the possibility to participate in standardization activities on national, European and global level. The membership in SIS will give you the opportunity to influence future standards and gain access to early stage information about developments within your field.

Get to know the finished work

We offer our customers everything in connection with standards and their application. You can purchase all the publications you need from us - everything from individual standards, technical reports and standard packages through to manuals and online services. Our web service e-nav gives you access to an easy-to-navigate library where all standards that are relevant to your company are available. Standards and manuals are sources of knowledge. We sell them.

Increase understanding and improve perception

With SIS you can undergo either shared or in-house training in the content and application of standards. Thanks to our proximity to international development and ISO you receive the right knowledge at the right time, direct from the source. With our knowledge about the potential of standards, we assist our customers in creating tangible benefit and profitability in their organisations.

If you want to know more about SIS, or how standards can streamline your organisation, please visit www.sis.se or contact us on phone +46 (0)8-555 523 00



Den internationella standarden ISO 4675:2017 gäller som svensk standard. Detta dokument innehåller den officiella engelska versionen av ISO 4675:2017.

The International Standard ISO 4675:2017 has the status of a Swedish Standard. This document contains the official English version of ISO 4675:2017.

© Copyright/Upphovsrätten till denna produkt tillhör SIS, Swedish Standards Institute, Stockholm, Sverige. Användningen av denna produkt regleras av slutanvändarlicensen som återfinns i denna produkt, se standardens sista sidor.

© Copyright SIS, Swedish Standards Institute, Stockholm, Sweden. All rights reserved. The use of this product is governed by the end-user licence for this product. You will find the licence in the end of this document.

Upplysningar om sakinnehållet i standarden lämnas av SIS, Swedish Standards Institute, telefon 08-555 520 00. Standarder kan beställas hos SIS som även lämnar allmänna upplysningar om svensk och utländsk standard.

Information about the content of the standard is available from the Swedish Standards Institute (SIS), telephone +46 8 555 520 00. Standards may be ordered from SIS, who can also provide general information about Swedish and foreign standards.

Denna standard är framtagen av kommittén för Gummi och gummiprodukter, SIS/TK 154.

Har du synpunkter på innehållet i den här standarden, vill du delta i ett kommande revideringsarbete eller vara med och ta fram andra standarder inom området? Gå in på www.sis.se - där hittar du mer information.

Contents		Page
Foreword	v
1	Scope	1
2	Normative references	1
3	Terms and definitions	1
4	Principle	1
5	Apparatus	1
6	Test pieces	2
7	Time-interval between manufacture and testing	2
8	Conditioning of test pieces	2
9	Procedure	2
10	Assessment of damage	3
	10.1 Depth of crack	3
	10.2 Number of cracks.....	3
	10.3 Length of crack.....	3
11	Test report	3

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see www.iso.org/directives).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see www.iso.org/patents).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation on the voluntary nature of standards, the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the World Trade Organization (WTO) principles in the Technical Barriers to Trade (TBT) see the following URL: www.iso.org/iso/foreword.html.

This document was prepared by Technical Committee ISO/TC 45, *Rubber and rubber products*, Subcommittee SC 4, *Products (other than hoses)*.

This third edition cancels and replaces the second edition (ISO 4675:1990), which has been technically revised.

The main changes compared to the previous edition are as follows:

- a WARNING has been inserted before the scope;
- [Clause 3](#) has been added;
- in [Figure 2](#), the dimension of H has been corrected.

Rubber- or plastics-coated fabrics — Low-temperature bend test

WARNING — Persons using this document should be familiar with normal laboratory practice. This document does not purport to address all of the safety problems, if any, associated with its use. It is the responsibility of the user to establish appropriate safety and health practices and to ensure compliance with any national regulatory conditions.

1 Scope

This document specifies a method for determining the ability of fabrics coated with rubber or plastics to resist the effect of low temperature when subjected to bending at specified temperatures after definite periods of exposure. This method is applicable to material with a thickness within the range 0,1 mm to 2,2 mm. For materials of greater thickness than this, modifications to the standard equipment apply (see [9.2](#), third paragraph).

Because fabrics coated with rubber or plastics are used in different applications requiring low temperature flexing, no general relationship between this test and service performance can be given or implied.

2 Normative references

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 2231, *Rubber- or plastics-coated fabrics — Standard atmospheres for conditioning and testing*

ISO 2286-3, *Rubber- or plastics-coated fabrics — Determination of roll characteristics — Part 3: Method for determination of thickness*

3 Terms and definitions

No terms and definitions are listed in this document.

ISO and IEC maintain terminological databases for use in standardization at the following addresses:

- ISO Online browsing platform: available at <http://www.iso.org/obp>
- IEC Electropedia: available at <http://www.electropedia.org/>

4 Principle

Test pieces, after conditioning, are exposed to low temperature for a predetermined period. Subsequently, the chilled test piece is subjected to a bending test, followed by examination.

5 Apparatus

5.1 Cold chamber, in which the test pieces are exposed to low temperature, sufficient in size to contain the bending fixture used for testing the test pieces and to permit the operation of the fixture to bend the test piece without removal from the chamber.

The cold chamber shall also have sufficient work space to permit the conditioning of test pieces as outlined in [Clause 8](#). It shall be capable of maintaining a uniform atmosphere of cold air or any other suitable gas at specified temperatures to within a tolerance of ± 1 °C.

SS-ISO 4675:2018 (E)

5.2 Bending jig, for bending the test pieces, as shown in [Figure 1](#) and [Figure 2](#).

Masses, mass tolerances and dimensions shall be as specified in [Figure 2](#).

5.3 Glass plates, of sufficient number, having dimensions of approximately 125 mm × 175 mm, for use when conditioning all test pieces.

The thickness of the glass plates shall be such as to permit easy handling.

5.4 Gloves, for handling test pieces within the cold chamber.

The gloves will be conditioned at the same temperature as the test pieces. A second pair of gloves at room temperature shall therefore be available for wearing within the cold gloves as protection for the operator.

6 Test pieces

Take three test pieces, each measuring 25 mm × 100 mm, equally spaced across the working width of the sample and with their lengths parallel to the longitudinal direction of the coated fabric, unless otherwise specified.

7 Time-interval between manufacture and testing

7.1 For all test purposes, the minimum time between manufacture and testing shall be 16 h.

7.2 For non-product tests, the maximum time between manufacture and testing shall be 4 weeks; for evaluations intended to be comparable, each test, as far as possible, shall be carried out after the same time-interval.

7.3 For product tests, whenever possible, the time between manufacturing and testing shall not exceed 3 months. In other cases, tests shall be made within 2 months of the date of receipt of the products by the customer.

8 Conditioning of test pieces

Immediately prior to testing, condition the test pieces in one of the standard atmospheres defined in ISO 2231.

9 Procedure

9.1 Measure the thickness of each test specimen in accordance with ISO 2286-3. Place the three conditioned test pieces between glass plates ([5.3](#)), with sufficient space between each test piece to permit the passage of air during the conditioning period. Place the glass plates with the test pieces held in position, the bending jig ([5.2](#)) and the cold gloves ([5.4](#)) in the cold chamber ([5.1](#)). Unless otherwise specified, expose them for 4 h to the specified test temperature.

9.2 At the termination of the exposure period and without taking them out of the test chamber, remove the test pieces from between the glass plates one at a time (CAUTION, see below) and place in the bending jig with the flexing plate held in the open position by the trigger pin. Unless otherwise specified, in the case of substrates coated on one side only, place the coated side away from the mandrel. In the case of double-coated fabrics, either or both surfaces may be evaluated unless otherwise specified.

CAUTION — Gloves shall be worn at all times when handling test pieces prior to making the bend test.