

# SVENSK STANDARD

## SS-EN 10217-3:2019

Fastställt/Approved: 2019-04-23  
Utgåva/Edition: 2  
Språk/Language: engelska/English  
ICS: 23.040.10;77.140.75

---

### **Svetsade rör av stål för tryckändamål – Tekniska leveransbestämmelser –**

**Del 3: Elektriskt motståndssvetsade och pulverbågs svetsade rör av legerade finkornstål med fordrade rums-, hög- och lågtemperaturregenskaper**

### **Welded steel tubes for pressure purposes – Technical delivery conditions –**

**Part 3: Electric welded and submerged arc welded alloy fine grain steel tubes with specified room, elevated and low temperature properties**

This preview is downloaded from [www.sis.se](http://www.sis.se). Buy the entire standard via <https://www.sis.se/std-80011438>

# Standarder får världen att fungera

*SIS (Swedish Standards Institute) är en fristående ideell förening med medlemmar från både privat och offentlig sektor. Vi är en del av det europeiska och globala nätverk som utarbetar internationella standarder. Standarder är dokumenterad kunskap utvecklad av framstående aktörer inom industri, näringsliv och samhälle och befrämjar handel över gränser, bidrar till att processer och produkter blir säkrare samt effektiviserar din verksamhet.*

## Delta och påverka

Som medlem i SIS har du möjlighet att påverka framtida standarder inom ditt område på nationell, europeisk och global nivå. Du får samtidigt tillgång till tidig information om utvecklingen inom din bransch.

## Ta del av det färdiga arbetet

Vi erbjuder våra kunder allt som rör standarder och deras tillämpning. Hos oss kan du köpa alla publikationer du behöver – allt från enskilda standarder, tekniska rapporter och standardpaket till handböcker och onlinetjänster. Genom vår webbtjänst e-nav får du tillgång till ett lättnavigerat bibliotek där alla standarder som är aktuella för ditt företag finns tillgängliga. Standarder och handböcker är källor till kunskap. Vi säljer dem.

## Utveckla din kompetens och lyckas bättre i ditt arbete

Hos SIS kan du gå öppna eller företagsinterna utbildningar kring innehåll och tillämpning av standarder. Genom vår närhet till den internationella utvecklingen och ISO får du rätt kunskap i rätt tid, direkt från källan. Med vår kunskap om standarders möjligheter hjälper vi våra kunder att skapa verklig nytta och lönsamhet i sina verksamheter.

**Vill du veta mer om SIS eller hur standarder kan effektivisera din verksamhet är du välkommen in på [www.sis.se](http://www.sis.se) eller ta kontakt med oss på tel 08-555 523 00.**



# Standards make the world go round

*SIS (Swedish Standards Institute) is an independent non-profit organisation with members from both the private and public sectors. We are part of the European and global network that draws up international standards. Standards consist of documented knowledge developed by prominent actors within the industry, business world and society. They promote cross-border trade, they help to make processes and products safer and they streamline your organisation.*

## Take part and have influence

As a member of SIS you will have the possibility to participate in standardization activities on national, European and global level. The membership in SIS will give you the opportunity to influence future standards and gain access to early stage information about developments within your field.

## Get to know the finished work

We offer our customers everything in connection with standards and their application. You can purchase all the publications you need from us - everything from individual standards, technical reports and standard packages through to manuals and online services. Our web service e-nav gives you access to an easy-to-navigate library where all standards that are relevant to your company are available. Standards and manuals are sources of knowledge. We sell them.

## Increase understanding and improve perception

With SIS you can undergo either shared or in-house training in the content and application of standards. Thanks to our proximity to international development and ISO you receive the right knowledge at the right time, direct from the source. With our knowledge about the potential of standards, we assist our customers in creating tangible benefit and profitability in their organisations.

**If you want to know more about SIS, or how standards can streamline your organisation, please visit [www.sis.se](http://www.sis.se) or contact us on phone +46 (0)8-555 523 00**



Europastandarden EN 10217-3:2019 gäller som svensk standard. Detta dokument innehåller den officiella engelska versionen av EN 10217-3:2019.

Denna standard ersätter SS-EN 10217-3:2004, utgåva 1 och SS-EN 10217-3/A1:2005, utgåva 1.

The European Standard EN 10217-3:2019 has the status of a Swedish Standard. This document contains the official version of EN 10217-3:2019.

This standard supersedes the SS-EN 10217-3:2004, edition 1 and SS-EN 10217-3/A1:2005, edition 1.

© Copyright/Upphovsrätten till denna produkt tillhör SIS, Swedish Standards Institute, Stockholm, Sverige. Användningen av denna produkt regleras av slutanvändarlicensen som återfinns i denna produkt, se standardens sista sidor.

© Copyright SIS, Swedish Standards Institute, Stockholm, Sweden. All rights reserved. The use of this product is governed by the end-user licence for this product. You will find the licence in the end of this document.

*Upplysningar om sakinnehållet i standarden lämnas av SIS, Swedish Standards Institute, telefon 08-555 520 00. Standarder kan beställas hos SIS som även lämnar allmänna upplysningar om svensk och utländsk standard.*

*Information about the content of the standard is available from the Swedish Standards Institute (SIS), telephone +46 8 555 520 00. Standards may be ordered from SIS, who can also provide general information about Swedish and foreign standards.*

Denna standard är framtagen av kommittén för Tryckkärlsstål, SIS/TK 137.

Har du synpunkter på innehållet i den här standarden, vill du delta i ett kommande revideringsarbete eller vara med och ta fram andra standarder inom området? Gå in på [www.sis.se](https://www.sis.se) - där hittar du mer information.



EUROPEAN STANDARD

EN 10217-3

NORME EUROPÉENNE

EUROPÄISCHE NORM

April 2019

ICS 23.040.10; 77.140.75

Supersedes EN 10217-3:2002

English Version

## Welded steel tubes for pressure purposes - Technical delivery conditions - Part 3: Electric welded and submerged arc welded alloy fine grain steel tubes with specified room, elevated and low temperature properties

Tubes soudés en acier pour service sous pression - Conditions techniques de livraison - Partie 3: Tubes en acier en acier allié à grains fins, soudés électriquement et soudés à l'arc immergé avec caractéristiques spécifiées à basse température et température élevée

Geschweißte Stahlrohre für Druckbeanspruchungen - Technische Lieferbedingungen - Teil 3: Elektrisch geschweißte und unterpulvergeschweißte Rohre aus legierten Feinkornbaustählen mit festgelegten Eigenschaften bei Raum-, erhöhten und tiefen Temperaturen

This European Standard was approved by CEN on 25 February 2019.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the CEN-CENELEC Management Centre or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the CEN-CENELEC Management Centre has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, Former Yugoslav Republic of Macedonia, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Serbia, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and United Kingdom.



EUROPEAN COMMITTEE FOR STANDARDIZATION  
COMITÉ EUROPÉEN DE NORMALISATION  
EUROPÄISCHES KOMITEE FÜR NORMUNG

**CEN-CENELEC Management Centre: Rue de la Science 23, B-1040 Brussels**

**SS-EN 10217-3:2019 (E)**

<b>Contents</b>	<b>Page</b>
European foreword.....	4
<b>1 Scope</b> .....	<b>6</b>
<b>2 Normative references</b> .....	<b>6</b>
<b>3 Terms and definitions</b> .....	<b>8</b>
<b>4 Symbols</b> .....	<b>9</b>
<b>5 Classification and designation</b> .....	<b>9</b>
5.1 Classification.....	9
5.2 Designation.....	9
<b>6 Information to be supplied by the purchaser</b> .....	<b>9</b>
6.1 Mandatory information.....	9
6.2 Options.....	10
6.3 Example of an order.....	11
<b>7 Manufacturing process</b> .....	<b>11</b>
7.1 Steelmaking process.....	11
7.2 Tube manufacture and delivery conditions.....	11
7.3 Non Destructive Testing Personnel Requirements.....	12
<b>8 Requirements</b> .....	<b>13</b>
8.1 General.....	13
8.2 Chemical composition.....	13
8.2.1 Cast analysis.....	13
8.2.2 Product analysis.....	15
8.3 Grain size.....	15
8.4 Mechanical properties.....	15
8.5 Appearance and internal soundness.....	18
8.5.1 Weld seam.....	18
8.5.2 Tube surface.....	18
8.5.3 Internal soundness.....	19
8.6 Straightness.....	19
8.7 Preparation of ends.....	19
8.8 Dimensions, masses and tolerances.....	20
8.8.1 Diameters and wall thickness.....	20
8.8.2 Mass.....	26
8.8.3 Lengths.....	26
8.8.4 Tolerances.....	26
<b>9 Inspection</b> .....	<b>28</b>
9.1 Type of inspection.....	28
9.2 Inspection documents.....	29
9.2.1 Types of inspection documents.....	29
9.2.2 Content of inspection documents.....	29
9.3 Summary of inspection and testing.....	29
<b>10 Sampling</b> .....	<b>32</b>
10.1 Frequency of tests.....	32
10.1.1 Test unit.....	32
10.1.2 Number of sample tubes per test unit.....	32
10.2 Preparation of samples and test pieces.....	32
10.2.1 Selection and preparation of samples for product analysis.....	32

<b>10.2.2</b>	<b>Location, orientation and preparation of samples and test pieces for mechanical tests .....</b>	<b>32</b>
<b>11</b>	<b>Verification of test methods .....</b>	<b>34</b>
<b>11.1</b>	<b>Chemical analysis .....</b>	<b>34</b>
<b>11.2</b>	<b>Tensile test.....</b>	<b>34</b>
<b>11.2.1</b>	<b>Tensile test on the tube body .....</b>	<b>34</b>
<b>11.2.2</b>	<b>Transverse tensile test on the weld.....</b>	<b>35</b>
<b>11.3</b>	<b>Flattening test.....</b>	<b>35</b>
<b>11.4</b>	<b>Ring tensile test.....</b>	<b>35</b>
<b>11.5</b>	<b>Drift expanding test.....</b>	<b>35</b>
<b>11.6</b>	<b>Ring expanding test .....</b>	<b>36</b>
<b>11.7</b>	<b>Weld bend test.....</b>	<b>36</b>
<b>11.8</b>	<b>Impact test .....</b>	<b>36</b>
<b>11.9</b>	<b>Leak tightness test .....</b>	<b>37</b>
<b>11.9.1</b>	<b>Hydrostatic test.....</b>	<b>37</b>
<b>11.9.2</b>	<b>Electromagnetic test.....</b>	<b>37</b>
<b>11.10</b>	<b>Dimensional inspection .....</b>	<b>37</b>
<b>11.11</b>	<b>Visual examination .....</b>	<b>38</b>
<b>11.12</b>	<b>Non-Destructive Testing.....</b>	<b>38</b>
<b>11.12.1</b>	<b>Non-Destructive Testing of HFW tubes.....</b>	<b>38</b>
<b>11.12.2</b>	<b>Non-destructive testing of SAW tubes .....</b>	<b>38</b>
<b>11.13</b>	<b>Material identification.....</b>	<b>39</b>
<b>11.14</b>	<b>Retests, sorting and reprocessing .....</b>	<b>39</b>
<b>12</b>	<b>Marking.....</b>	<b>40</b>
<b>12.1</b>	<b>Marking to be applied.....</b>	<b>40</b>
<b>12.2</b>	<b>Additional marking.....</b>	<b>40</b>
<b>13</b>	<b>Protection.....</b>	<b>40</b>
<b>Annex A</b>	<b>(normative) Qualification of welding procedure for SAW tube production.....</b>	<b>41</b>
<b>A.1</b>	<b>General .....</b>	<b>41</b>
<b>A.2</b>	<b>Welding procedure specification .....</b>	<b>41</b>
<b>A.3</b>	<b>Preparation of sample tube and sample assessment.....</b>	<b>42</b>
<b>A.4</b>	<b>Inspection and testing of the weld .....</b>	<b>44</b>
<b>A.5</b>	<b>Weld test pieces .....</b>	<b>44</b>
<b>A.6</b>	<b>Test methods.....</b>	<b>44</b>
<b>A.7</b>	<b>Test acceptance levels .....</b>	<b>45</b>
<b>A.8</b>	<b>Range of use of qualified procedures.....</b>	<b>47</b>
<b>A.9</b>	<b>Qualification record .....</b>	<b>48</b>
<b>Annex B</b>	<b>(normative) Elevated temperature properties for steel grades P275NL1 and NL2 .....</b>	<b>49</b>
<b>Annex C</b>	<b>(informative) Technical changes from the previous edition.....</b>	<b>50</b>
<b>C.1</b>	<b>Introduction .....</b>	<b>50</b>
<b>C.2</b>	<b>Technical changes .....</b>	<b>50</b>
<b>Annex ZA</b>	<b>(informative) Relationship between this European Standard and the Essential Requirements of 2014/68/EU .....</b>	<b>52</b>
	<b>Bibliography.....</b>	<b>53</b>

## SS-EN 10217-3:2019 (E)

### European foreword

This document (EN 10217-3:2019) has been prepared by Technical Committee CEN/TC 459 “ECISS - European Committee for Iron and Steel Standardization”<sup>1</sup>, the secretariat of which is held by AFNOR.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by October 2019, and conflicting national standards shall be withdrawn at the latest by October 2019.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. CEN shall not be held responsible for identifying any or all such patent rights.

This document supersedes EN 10217-3:2002.

This document has been prepared under a mandate given to CEN by the European Commission and the European Free Trade Association, and supports essential requirements of EU Directive 2014/68/EU.

For relationship with EU Directive 2014/68/EU (formerly 97/23/EC), see informative Annex ZA, which is an integral part of this document.

This European Standard consists of the following parts, under the general title *Welded steel tubes for pressure purposes – Technical delivery conditions*:

*Part 1: Electric welded and submerged arc welded non-alloy steel tubes with specified room temperature properties*

*Part 2: Electric welded non-alloy and alloy steel tubes with specified elevated temperature properties*

*Part 3: Electric welded and submerged arc welded alloy fine grain steel tubes with specified room, elevated and low temperature properties*

*Part 4: Electric welded non-alloy steel tubes with specified low temperature properties*

*Part 5: Submerged arc welded non-alloy and alloy steel tubes with specified elevated temperature properties*

*Part 6: Submerged arc welded non-alloy steel tubes with specified low temperature properties*

*Part 7: Stainless steel tubes*

Another European Standard series covering tubes for pressure purposes is:

EN 10216, *Seamless steel tubes for pressure purposes*

According to the CEN-CENELEC Internal Regulations, the national standards organisations of the following countries are bound to implement this European Standard: Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, Former Yugoslav Republic of Macedonia,

---

<sup>1</sup> Through its subcommittee SC 10 “Steel tubes, and iron and steel fittings” (secretariat: UNI)



France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Serbia, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and the United Kingdom.

## SS-EN 10217-3:2019 (E)

### 1 Scope

This document specifies the technical delivery conditions for two test categories of electric welded and submerged arc longitudinally (SAWL) or helically (SAWH) welded tubes of circular cross section, made from weldable fine grain steel.

NOTE 1 These tube grades are intended to support the essential requirements of EU Directive 2014/68/EU in respect of pressure equipment covered under all relevant Categories as set out in Article 13 of that Directive.

NOTE 2 Once this standard is published in the Official Journal of the European Union (OJEU), presumption of conformity to the Essential Safety Requirements (ESR) of Directive 2014/68/EU is limited to the technical data for the materials in this standard and does not presume adequacy of the material for a specific item of pressure equipment. Consequently, the assessment of the technical data stated in this material standard against the design requirements of a specific item of equipment to verify that the ESRs of the Pressure Equipment Directive are satisfied, needs to be done by the designer or manufacturer of the pressure equipment, taking also into account any subsequent processing procedures which may affect properties of the base materials.

### 2 Normative references

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

EN 10020, *Definition and classification of grades of steel*

EN 10021:2006, *General technical delivery conditions for steel products*

EN 10027-1, *Designation systems for steels — Part 1: Steel names*

EN 10027-2, *Designation systems for steels — Part 2: Numerical system*

EN 10168:2004, *Steel products — Inspection documents — List of information and description*

EN 10204:2004, *Metallic products — Types of inspection documents*

EN 10220, *Seamless and welded steel tubes — Dimensions and masses per unit length*

CEN/TR 10261, *Iron and steel — European standards for the determination of chemical composition*

EN 10266, *Steel tubes, fittings and structural hollow sections — Symbols and definitions of terms for use in product standards*

EN ISO 148-1:2016, *Metallic materials — Charpy pendulum impact test — Part 1: Test method (ISO 148-1:2016)*

EN ISO 377:2017, *Steel and steel products — Location and preparation of samples and test pieces for mechanical testing (ISO 377:2017)*

EN ISO 643:2012, *Steels — Micrographic determination of the apparent grain size (ISO 643:2012)*

EN ISO 2566-1:1999, *Steel — Conversion of elongation values — Part 1: Carbon and low alloy steels (ISO 2566-1:1984)*

EN ISO 4885, *Ferrous materials — Heat treatments — Vocabulary (ISO 4885)*

EN ISO 5173:2010, *Destructive tests on welds in metallic materials — Bend tests (ISO 5173:2009)*

EN ISO 6892-1:2016, *Metallic materials — Tensile testing — Part 1: Method of test at room temperature (ISO 6892-1:2016)*

EN ISO 6892-2:2018, *Metallic materials — Tensile testing — Part 2: Method of test at elevated temperature (ISO 6892-2:2018)*

EN ISO 8492:2013, *Metallic materials — Tube — Flattening test (ISO 8492:2013)*

EN ISO 8493:2004, *Metallic materials — Tube — Drift-expanding test (ISO 8493:1998)*

EN ISO 8495:2013, *Metallic materials — Tube — Ring-expanding test (ISO 8495:2013)*

EN ISO 8496:2013, *Metallic materials — Tube — Ring tensile test (ISO 8496:2013)*

EN ISO 10893-1:2011, *Non-destructive testing of steel tubes — Part 1: Automated electromagnetic testing of seamless and welded (except submerged arc-welded) steel tubes for the verification of hydraulic leaktightness (ISO 10893-1:2011)*

EN ISO 10893-2:2011, *Non-destructive testing of steel tubes — Part 2: Automated eddy current testing of seamless and welded (except submerged arc-welded) steel tubes for the detection of imperfections (ISO 10893-2:2011)*

EN ISO 10893-3:2011, *Non-destructive testing of steel tubes — Part 3: Automated full peripheral flux leakage testing of seamless and welded (except submerged arc-welded) ferromagnetic steel tubes for the detection of longitudinal and/or transverse imperfections (ISO 10893-3:2011)*

EN ISO 10893-6:2011, *Non-destructive testing of steel tubes — Part 6: Radiographic testing of the weld seam of welded steel tubes for the detection of imperfections (ISO 10893-6:2011)*

EN ISO 10893-7:2011, *Non-destructive testing of steel tubes — Part 7: Digital radiographic testing of the weld seam of welded steel tubes for the detection of imperfections (ISO 10893-7:2011)*

EN ISO 10893-8:2011, *Non-destructive testing of steel tubes — Part 8: Automated ultrasonic testing of seamless and welded steel tubes for the detection of laminar imperfections (ISO 10893-8:2011)*

EN ISO 10893-9:2011, *Non-destructive testing of steel tubes — Part 9: Automated ultrasonic testing for the detection of laminar imperfections in strip/plate used for the manufacture of welded steel tubes (ISO 10893-9:2011)*

EN ISO 10893-10:2011, *Non-destructive testing of steel tubes — Part 10: Automated full peripheral ultrasonic testing of seamless and welded (except submerged arc-welded) steel tubes for the detection of longitudinal and/or transverse imperfections (ISO 10893-10:2011)*

EN ISO 10893-11:2011, *Non-destructive testing of steel tubes — Part 11: Automated ultrasonic testing of the weld seam of welded steel tubes for the detection of longitudinal and/or transverse imperfections (ISO 10893-11:2011)*

EN ISO 14174:2012, *Welding consumables — Fluxes for submerged arc welding and electroslag welding — Classification (ISO 14174:2012)*

EN ISO 14284, *Steel and iron — Sampling and preparation of samples for the determination of chemical composition (ISO 14284)*

EN ISO 17639:2013, *Destructive tests on welds in metallic materials — Macroscopic and microscopic examination of welds (ISO 17639:2003)*