

SVENSK STANDARD

SS-EN 10217-6:2019

Fastställt/Approved: 2019-04-23
Utgåva/Edition: 2
Språk/Language: engelska/English
ICS: 23.040.10;77.140.75

Svetsade rör av stål för tryckändamål – Tekniska leveransbestämmelser – Del 6: Pulverbågsvetsade rör av olegerade stål med fordrade lågtemperaturegenskaper

**Welded steel tubes for pressure purposes – Technical delivery
conditions –
Part 6: Submerged arc welded non-alloy steel tubes with
specified low temperature properties**

This preview is downloaded from www.sis.se. Buy the entire standard via <https://www.sis.se/std-80011441>

Standarder får världen att fungera

SIS (Swedish Standards Institute) är en fristående ideell förening med medlemmar från både privat och offentlig sektor. Vi är en del av det europeiska och globala nätverk som utarbetar internationella standarder. Standarder är dokumenterad kunskap utvecklad av framstående aktörer inom industri, näringsliv och samhälle och befrämjar handel över gränser, bidrar till att processer och produkter blir säkrare samt effektiviserar din verksamhet.

Delta och påverka

Som medlem i SIS har du möjlighet att påverka framtida standarder inom ditt område på nationell, europeisk och global nivå. Du får samtidigt tillgång till tidig information om utvecklingen inom din bransch.

Ta del av det färdiga arbetet

Vi erbjuder våra kunder allt som rör standarder och deras tillämpning. Hos oss kan du köpa alla publikationer du behöver – allt från enskilda standarder, tekniska rapporter och standardpaket till handböcker och onlinetjänster. Genom vår webbtjänst e-nav får du tillgång till ett lättnavigerat bibliotek där alla standarder som är aktuella för ditt företag finns tillgängliga. Standarder och handböcker är källor till kunskap. Vi säljer dem.

Utveckla din kompetens och lyckas bättre i ditt arbete

Hos SIS kan du gå öppna eller företagsinterna utbildningar kring innehåll och tillämpning av standarder. Genom vår närhet till den internationella utvecklingen och ISO får du rätt kunskap i rätt tid, direkt från källan. Med vår kunskap om standarders möjligheter hjälper vi våra kunder att skapa verklig nytta och lönsamhet i sina verksamheter.

Vill du veta mer om SIS eller hur standarder kan effektivisera din verksamhet är du välkommen in på www.sis.se eller ta kontakt med oss på tel 08-555 523 00.



Standards make the world go round

SIS (Swedish Standards Institute) is an independent non-profit organisation with members from both the private and public sectors. We are part of the European and global network that draws up international standards. Standards consist of documented knowledge developed by prominent actors within the industry, business world and society. They promote cross-border trade, they help to make processes and products safer and they streamline your organisation.

Take part and have influence

As a member of SIS you will have the possibility to participate in standardization activities on national, European and global level. The membership in SIS will give you the opportunity to influence future standards and gain access to early stage information about developments within your field.

Get to know the finished work

We offer our customers everything in connection with standards and their application. You can purchase all the publications you need from us - everything from individual standards, technical reports and standard packages through to manuals and online services. Our web service e-nav gives you access to an easy-to-navigate library where all standards that are relevant to your company are available. Standards and manuals are sources of knowledge. We sell them.

Increase understanding and improve perception

With SIS you can undergo either shared or in-house training in the content and application of standards. Thanks to our proximity to international development and ISO you receive the right knowledge at the right time, direct from the source. With our knowledge about the potential of standards, we assist our customers in creating tangible benefit and profitability in their organisations.

If you want to know more about SIS, or how standards can streamline your organisation, please visit www.sis.se or contact us on phone +46 (0)8-555 523 00



Europastandarden EN 10217-6:2019 gäller som svensk standard. Detta dokument innehåller den officiella engelska versionen av EN 10217-6:2019.

Denna standard ersätter SS-EN 10217-6:2004, utgåva 1 och SS-EN 10217-6/A1:2005, utgåva 1.

The European Standard EN 10217-6:2019 has the status of a Swedish Standard. This document contains the official version of EN 10217-6:2019.

This standard supersedes the SS-EN 10217-6:2004, edition 1 and SS-EN 10217-6/A1:2005, edition 1.

© Copyright/Upphovsrätten till denna produkt tillhör SIS, Swedish Standards Institute, Stockholm, Sverige. Användningen av denna produkt regleras av slutanvändarlicensen som återfinns i denna produkt, se standardens sista sidor.

© Copyright SIS, Swedish Standards Institute, Stockholm, Sweden. All rights reserved. The use of this product is governed by the end-user licence for this product. You will find the licence in the end of this document.

Upplysningar om sakinnehållet i standarden lämnas av SIS, Swedish Standards Institute, telefon 08-555 520 00. Standarder kan beställas hos SIS som även lämnar allmänna upplysningar om svensk och utländsk standard.

Information about the content of the standard is available from the Swedish Standards Institute (SIS), telephone +46 8 555 520 00. Standards may be ordered from SIS, who can also provide general information about Swedish and foreign standards.

Denna standard är framtagen av kommittén för Tryckkärlsstål, SIS/TK 137.

Har du synpunkter på innehållet i den här standarden, vill du delta i ett kommande revideringsarbete eller vara med och ta fram andra standarder inom området? Gå in på www.sis.se - där hittar du mer information.

EUROPEAN STANDARD

EN 10217-6

NORME EUROPÉENNE

EUROPÄISCHE NORM

April 2019

ICS 23.040.10; 77.140.75

Supersedes EN 10217-6:2002

English Version

Welded steel tubes for pressure purposes - Technical
delivery conditions - Part 6: Submerged arc welded non-
alloy steel tubes with specified low temperature
properties

Tubes soudés en acier pour service sous pression-
Conditions techniques de livraison - Partie 6: Tubes
soudés à l'arc sous flux en aciers non allié avec
caractéristiques spécifiées à basse température

Geschweißte Stahlrohre für Druckbeanspruchungen -
Technische Lieferbedingungen - Teil 6:
Unterpulvergeschweißte Rohre aus unlegierten
Stählen mit festgelegten Eigenschaften bei tiefen
Temperaturen

This European Standard was approved by CEN on 25 February 2019.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the CEN-CENELEC Management Centre or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the CEN-CENELEC Management Centre has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, Former Yugoslav Republic of Macedonia, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Serbia, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and United Kingdom.



EUROPEAN COMMITTEE FOR STANDARDIZATION
COMITÉ EUROPÉEN DE NORMALISATION
EUROPÄISCHES KOMITEE FÜR NORMUNG

CEN-CENELEC Management Centre: Rue de la Science 23, B-1040 Brussels

SS-EN 10217-6:2019 (E)

Contents	Page
European foreword.....	4
1 Scope.....	5
2 Normative references.....	5
3 Terms and definitions	6
4 Symbols.....	7
5 Classification and designation.....	7
5.1 Classification.....	7
5.2 Designation.....	7
6 Information to be supplied by the purchaser	7
6.1 Mandatory information	7
6.2 Options.....	8
6.3 Example of an order	8
7 Manufacturing process.....	8
7.1 Steelmaking process	8
7.2 Tube manufacture and delivery conditions.....	9
7.3 Non Destructive Testing Personnel Requirements	10
8 Requirements	10
8.1 General.....	10
8.2 Chemical composition	11
8.2.1 Cast analysis.....	11
8.2.2 Product analysis	11
8.3 Mechanical properties.....	12
8.4 Appearance and internal soundness.....	13
8.4.1 Weld seam.....	13
8.4.2 Tube surface.....	13
8.4.3 Internal soundness.....	14
8.5 Straightness.....	14
8.6 Preparation of ends.....	14
8.7 Dimensions, masses and tolerances.....	15
8.7.1 Diameter and wall thickness.....	15
8.7.2 Mass.....	15
8.7.3 Lengths.....	15
8.7.4 Tolerances	15
9 Inspection	19
9.1 Type of inspection.....	19
9.2 Inspection documents	19
9.2.1 Types of inspection documents.....	19
9.2.2 Content of inspection documents.....	19
9.3 Summary of inspection and verification testing.....	20
10 Sampling.....	22
10.1 Frequency of tests	22
10.1.1 Test unit.....	22
10.1.2 Number of sample tubes per test unit	22
10.2 Preparation of samples and test pieces	22
10.2.1 Selection and preparation of samples for product analysis	22

10.2.2	Location, orientation and preparation of samples and test pieces for mechanical tests	22
11	Verification of test methods.....	24
11.1	Chemical analysis	24
11.2	Tensile test on the tube body	24
11.3	Transverse tensile test on the weld.....	24
11.4	Weld bend test	24
11.5	Impact test.....	24
11.6	Hydrostatic leak tightness test	25
11.7	Dimensional inspection.....	25
11.8	Visual examination	26
11.9	Non-Destructive Testing	26
11.9.1	Non-Destructive Testing of the weld seam.....	26
11.9.2	Non-Destructive Testing for the detection of laminations for tubes of test category 2	26
11.9.3	Supply of strip end welds in SAWH tubes	27
11.10	Retests, sorting and reprocessing	27
12	Marking.....	27
12.1	Marking to be applied	27
12.2	Additional marking.....	27
13	Protection.....	27
Annex A	(normative) Qualification of welding procedure.....	28
A.1	General	28
A.2	Welding procedure specification.....	28
A.3	Preparation of sample tube and sample assessment	30
A.4	Inspection and testing of the weld.....	30
A.5	Weld test pieces.....	31
A.6	Test methods.....	31
A.7	Test acceptance levels.....	32
A.8	Range of use of qualified procedures	34
A.9	Qualification record.....	34
Annex B	(informative) Technical changes from the previous edition.....	35
B.1	Introduction	35
B.2	Technical changes	35
Annex ZA	(informative) Relationship between this European Standard and the Essential Requirements of 2014/68/EU	37
Bibliography	38

SS-EN 10217-6:2019 (E)

European foreword

This document (EN 10217-6:2019) has been prepared by Technical Committee CEN/TC 459 “ECISS - European Committee for Iron and Steel Standardization”¹, the secretariat of which is held by AFNOR.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by October 2019, and conflicting national standards shall be withdrawn at the latest by October 2019.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. CEN shall not be held responsible for identifying any or all such patent rights.

This document supersedes EN 10217-6:2002.

This document has been prepared under a mandate given to CEN by the European Commission and the European Free Trade Association, and supports essential requirements of EU Directive 2014/68/EU.

For relationship with EU Directive 2014/68/EU (formerly 97/23/EC), see informative Annex ZA, which is an integral part of this document.

This European Standard consists of the following parts, under the general title *Welded steel tubes for pressure purposes – Technical delivery conditions*:

Part 1: Electric welded and submerged arc welded non-alloy steel tubes with specified room temperature properties

Part 2: Electric welded non-alloy and alloy steel tubes with specified elevated temperature properties

Part 3: Electric welded and submerged arc welded alloy fine grain steel tubes with specified room, elevated and low temperature properties

Part 4: Electric welded non-alloy steel tubes with specified low temperature properties

Part 5: Submerged arc welded non-alloy and alloy steel tubes with specified elevated temperature properties

Part 6: Submerged arc welded non-alloy steel tubes with specified low temperature properties

Part 7: Stainless steel tubes

Another European Standard series covering tubes for pressure purposes is:

EN 10216, *Seamless steel tubes for pressure purposes*.

According to the CEN-CENELEC Internal Regulations, the national standards organisations of the following countries are bound to implement this European Standard: Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, Former Yugoslav Republic of Macedonia, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Serbia, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and the United Kingdom.

¹ Through its subcommittee SC 10 “Steel tubes, and iron and steel fittings” (secretariat: UNI)

1 Scope

This document specifies the technical delivery conditions for two test categories of submerged arc longitudinally (SAWL) or helically (SAWH) welded tubes of circular cross section, with specified low temperature properties, made from non-alloy quality steel.

NOTE 1 These tube grades are intended to support the essential requirements of EU Directive 2014/68/EU in respect of pressure equipment with specified low temperature properties (see Table 5), covered under all relevant Categories as set out in Article 13 of that Directive.

NOTE 2 Once this standard is published in the Official Journal of the European Union (OJEU), presumption of conformity to the Essential Safety Requirements (ESR) of Directive 2014/68/EU is limited to the technical data for the materials in this standard and does not presume adequacy of the material for a specific item of pressure equipment. Consequently, the assessment of the technical data stated in this material standard against the design requirements of this specific item of equipment to verify that the ESRs of the Pressure Equipment Directive are satisfied, needs to be done by the designer or manufacturer of the pressure equipment, taking also into account the subsequent manufacturing processes which may affect properties of the base materials.

2 Normative references

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

EN 10020, *Definition and classification of grades of steel*

EN 10021:2006, *General technical delivery conditions for steel products*

EN 10027-1, *Designation systems for steels — Part 1: Steel names*

EN 10027-2, *Designation systems for steels — Part 2: Numerical system*

EN 10168:2004, *Steel products — Inspection documents — List of information and description*

EN 10204:2004, *Metallic products — Types of inspection documents*

EN 10220, *Seamless and welded steel tubes — Dimensions and masses per unit length*

CEN/TR 10261, *Iron and steel — European standards for the determination of chemical composition*

EN 10266, *Steel tubes, fittings and structural hollow sections — Symbols and definitions of terms for use in product standards*

EN ISO 148-1:2016, *Metallic materials — Charpy pendulum impact test — Part 1: Test method (ISO 148-1:2016)*

EN ISO 377:2017, *Steel and steel products — Location and preparation of samples and test pieces for mechanical testing (ISO 377:2017)*

EN ISO 2566-1:1999, *Steel — Conversion of elongation values — Part 1: Carbon and low alloy steels (ISO 2566-1:1984)*

EN ISO 4885, *Ferrous materials — Heat treatments — Vocabulary (ISO 4885)*

EN ISO 5173:2010, *Destructive tests on welds in metallic materials — Bend tests (ISO 5173:2009)*

EN ISO 6892-1:2016, *Metallic materials — Tensile testing — Part 1: Method of test at room temperature (ISO 6892-1:2016)*

SS-EN 10217-6:2019 (E)

EN ISO 10893-6:2011, *Non-destructive testing of steel tubes — Part 6: Radiographic testing of the weld seam of welded steel tubes for the detection of imperfections (ISO 10893-6:2011)*

EN ISO 10893-7:2011, *Non-destructive testing of steel tubes — Part 7: Digital radiographic testing of the weld seam of welded steel tubes for the detection of imperfections (ISO 10893-7:2011)*

EN ISO 10893-8:2011, *Non-destructive testing of steel tubes — Part 8: Automated ultrasonic testing of seamless and welded steel tubes for the detection of laminar imperfections (ISO 10893-8:2011)*

EN ISO 10893-9:2011, *Non-destructive testing of steel tubes — Part 9: Automated ultrasonic testing for the detection of laminar imperfections in strip/plate used for the manufacture of welded steel tubes (ISO 10893-9:2011)*

EN ISO 10893-11:2011, *Non-destructive testing of steel tubes — Part 11: Automated ultrasonic testing of the weld seam of welded steel tubes for the detection of longitudinal and/or transverse imperfections (ISO 10893-11:2011)*

EN ISO 14174:2012, *Welding consumables — Fluxes for submerged arc welding and electroslag welding — Classification (ISO 14174:2012)*

EN ISO 14284, *Steel and iron — Sampling and preparation of samples for the determination of chemical composition (ISO 14284)*

EN ISO 17639:2013, *Destructive tests on welds in metallic materials — Macroscopic and microscopic examination of welds (ISO 17639:2003)*

ISO 11484:2009, *Steel products — Employer's qualification system for non-destructive testing (NDT) personnel*

3 Terms and definitions

For the purpose of this document, the definitions given in EN 10020, EN 10021, EN 10266, EN ISO 4885 and the following apply.

ISO and IEC maintain terminological databases for use in standardization at the following addresses:

- IEC Electropedia: available at <http://www.electropedia.org/>
- ISO Online browsing platform: available at <http://www.iso.org/obp>

3.1 test category

classification that indicates the extent and level of inspection and testing

3.2 employer

organisation for which a person works on a regular basis

Note 1 to entry: The employer may be either the tube manufacturer or a third party organization providing services, such as Non-Destructive Testing (NDT).

3.3 SAW submerged-arc welded tube

tubular product having one or two longitudinal seams, or one helical seam, produced using the submerged-arc welding process

3.4

SAWH

submerged-arc helical welded tube

tubular product having one helical weld seam produced using the submerged-arc welding process

3.5

SAWL

submerged-arc longitudinal welded tube

tubular product having one or two longitudinal weld seams produced using the submerged-arc welding process

4 Symbols

For the purposes of this document, the symbols given in EN 10266 apply.

5 Classification and designation

5.1 Classification

In accordance with the classification system in EN 10020, the steel grades given in Tables 2 and 4 are classified as non-alloy quality steels.

5.2 Designation

5.2.1 For the tubes covered by this document the steel designation consists of:

— the number of this European Standard, e.g. EN 10217-6;

plus either:

— the steel name in accordance with EN 10027-1;

or:

— the steel number allocated in accordance with EN 10027-2.

5.2.2 The steel name is designated by

— the capital letter P for pressure purposes;

— the indication of the specified minimum yield strength expressed in MPa, (see Table 4);

— the symbol of the delivery condition for the steel grade concerned (see Table 1);

— the symbol L for low temperature.

6 Information to be supplied by the purchaser

6.1 Mandatory information

The following information shall be supplied by the purchaser at the time of enquiry and order:

- a) the quantity (mass, total length or number of tubes of set length);
- b) the term 'tube' and tube type, SAWL or SAWH;
- c) the dimensions (outside diameter D , wall thickness T) (see Table 6);