

# SVENSK STANDARD

## SS-EN 10225-1:2019

Fastställt/Approved: 2019-05-21  
Utgåva/Edition: 1  
Språk/Language: engelska/English  
ICS: 77.140.10

---

### **Svetsbara konstruktionsstål för fasta offshorekonstruktioner – Del 1: Plåt**

### **Weldable structural steels for fixed offshore structures – Technical delivery conditions – Part 1: Plates**

This preview is downloaded from [www.sis.se](http://www.sis.se). Buy the entire standard via <https://www.sis.se/std-80012018>

# Standarder får världen att fungera

*SIS (Swedish Standards Institute) är en fristående ideell förening med medlemmar från både privat och offentlig sektor. Vi är en del av det europeiska och globala nätverk som utarbetar internationella standarder. Standarder är dokumenterad kunskap utvecklad av framstående aktörer inom industri, näringsliv och samhälle och befrämjar handel över gränser, bidrar till att processer och produkter blir säkrare samt effektiviserar din verksamhet.*

## Delta och påverka

Som medlem i SIS har du möjlighet att påverka framtida standarder inom ditt område på nationell, europeisk och global nivå. Du får samtidigt tillgång till tidig information om utvecklingen inom din bransch.


## Ta del av det färdiga arbetet

Vi erbjuder våra kunder allt som rör standarder och deras tillämpning. Hos oss kan du köpa alla publikationer du behöver – allt från enskilda standarder, tekniska rapporter och standardpaket till handböcker och onlinetjänster. Genom vår webbtjänst e-nav får du tillgång till ett lättnavigerat bibliotek där alla standarder som är aktuella för ditt företag finns tillgängliga. Standarder och handböcker är källor till kunskap. Vi säljer dem.

## Utveckla din kompetens och lyckas bättre i ditt arbete

Hos SIS kan du gå öppna eller företagsinterna utbildningar kring innehåll och tillämpning av standarder. Genom vår närhet till den internationella utvecklingen och ISO får du rätt kunskap i rätt tid, direkt från källan. Med vår kunskap om standarders möjligheter hjälper vi våra kunder att skapa verklig nytta och lönsamhet i sina verksamheter.

**Vill du veta mer om SIS eller hur standarder kan effektivisera din verksamhet är du välkommen in på [www.sis.se](http://www.sis.se) eller ta kontakt med oss på tel 08-555 523 00.**



# Standards make the world go round

*SIS (Swedish Standards Institute) is an independent non-profit organisation with members from both the private and public sectors. We are part of the European and global network that draws up international standards. Standards consist of documented knowledge developed by prominent actors within the industry, business world and society. They promote cross-border trade, they help to make processes and products safer and they streamline your organisation.*

## Take part and have influence

As a member of SIS you will have the possibility to participate in standardization activities on national, European and global level. The membership in SIS will give you the opportunity to influence future standards and gain access to early stage information about developments within your field.

## Get to know the finished work

We offer our customers everything in connection with standards and their application. You can purchase all the publications you need from us - everything from individual standards, technical reports and standard packages through to manuals and online services. Our web service e-nav gives you access to an easy-to-navigate library where all standards that are relevant to your company are available. Standards and manuals are sources of knowledge. We sell them.

## Increase understanding and improve perception

With SIS you can undergo either shared or in-house training in the content and application of standards. Thanks to our proximity to international development and ISO you receive the right knowledge at the right time, direct from the source. With our knowledge about the potential of standards, we assist our customers in creating tangible benefit and profitability in their organisations.

**If you want to know more about SIS, or how standards can streamline your organisation, please visit [www.sis.se](http://www.sis.se) or contact us on phone +46 (0)8-555 523 00**



Europastandarden EN 10225-1:2019 gäller som svensk standard. Detta dokument innehåller den officiella engelska versionen av EN 10225-1:2019.

Denna standard ersätter SS-EN 10225:2009, utgåva 2.

The European Standard EN 10225-1:2019 has the status of a Swedish Standard. This document contains the official version of EN 10225-1:2019.

This standard supersedes the SS-EN 10225:2009, edition 2.

© Copyright/Upphovsrätten till denna produkt tillhör SIS, Swedish Standards Institute, Stockholm, Sverige. Användningen av denna produkt regleras av slutanvändarlicensen som återfinns i denna produkt, se standardens sista sidor.

© Copyright SIS, Swedish Standards Institute, Stockholm, Sweden. All rights reserved. The use of this product is governed by the end-user licence for this product. You will find the licence in the end of this document.

*Upplysningar om sakinnehållet i standarden lämnas av SIS, Swedish Standards Institute, telefon 08-555 520 00. Standarder kan beställas hos SIS som även lämnar allmänna upplysningar om svensk och utländsk standard.*

*Information about the content of the standard is available from the Swedish Standards Institute (SIS), telephone +46 8 555 520 00. Standards may be ordered from SIS, who can also provide general information about Swedish and foreign standards.*

Denna standard är framtagen av kommittén för Konstruktionsstål, SIS/TK 142.

Har du synpunkter på innehållet i den här standarden, vill du delta i ett kommande revideringsarbete eller vara med och ta fram andra standarder inom området? Gå in på [www.sis.se](https://www.sis.se) - där hittar du mer information.



EUROPEAN STANDARD

**EN 10225-1**

NORME EUROPÉENNE

EUROPÄISCHE NORM

May 2019

ICS 77.140.10

Supersedes EN 10225:2009

English Version

## Weldable structural steels for fixed offshore structures - Technical delivery conditions - Part 1: Plates

Aciers de construction soudables destinés à la  
fabrication de structures marines fixes - Conditions  
techniques de livraison - Partie 1 : Tôles

Schweißgeeignete Baustähle für feststehende Offshore-  
Konstruktionen - Technische Lieferbedingungen - Teil  
1: Bleche

This European Standard was approved by CEN on 23 December 2018.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the CEN-CENELEC Management Centre or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the CEN-CENELEC Management Centre has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, Former Yugoslav Republic of Macedonia, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Serbia, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and United Kingdom.



EUROPEAN COMMITTEE FOR STANDARDIZATION  
COMITÉ EUROPÉEN DE NORMALISATION  
EUROPÄISCHES KOMITEE FÜR NORMUNG

**CEN-CENELEC Management Centre: Rue de la Science 23, B-1040 Brussels**

<b>Contents</b>		Page
European foreword .....		4
<b>1</b>	<b>Scope</b> .....	5
<b>2</b>	<b>Normative references</b> .....	5
<b>3</b>	<b>Terms and definitions</b> .....	7
<b>4</b>	<b>Classification and designation</b> .....	8
<b>4.1</b>	<b>Classification</b> .....	8
<b>4.2</b>	<b>Designation</b> .....	8
<b>5</b>	<b>Information to be supplied by the purchaser</b> .....	9
<b>5.1</b>	<b>Mandatory information</b> .....	9
<b>5.2</b>	<b>Options</b> .....	9
<b>5.3</b>	<b>Example of an order</b> .....	10
<b>6</b>	<b>Manufacturing process</b> .....	10
<b>6.1</b>	<b>Steel manufacturing process</b> .....	10
<b>6.2</b>	<b>Qualification of personnel for NDT-activities</b> .....	10
<b>6.3</b>	<b>Delivery condition</b> .....	10
<b>6.4</b>	<b>Thickness limits</b> .....	11
<b>7</b>	<b>Requirements</b> .....	11
<b>7.1</b>	<b>General</b> .....	11
<b>7.2</b>	<b>Chemical composition</b> .....	11
<b>7.2.1</b>	<b>Heat analysis</b> .....	11
<b>7.2.2</b>	<b>Product analysis</b> .....	11
<b>7.2.3</b>	<b>Carbon equivalent values (CEV) and <math>P_{cm}</math></b> .....	12
<b>7.3</b>	<b>Mechanical properties</b> .....	12
<b>7.3.1</b>	<b>General</b> .....	12
<b>7.3.2</b>	<b>Post weld heat treatment (PWHT)</b> .....	12
<b>7.3.3</b>	<b>Strain age tests</b> .....	12
<b>7.3.4</b>	<b>Through-thickness testing</b> .....	12
<b>7.3.5</b>	<b>Fracture mechanic testing</b> .....	12
<b>7.3.6</b>	<b>Prequalification for arctic areas</b> .....	13
<b>7.4</b>	<b>Technological properties</b> .....	13
<b>7.4.1</b>	<b>Cold forming characteristics of steel plate</b> .....	13
<b>7.4.2</b>	<b>Hot forming procedures for steel plate</b> .....	13
<b>7.4.3</b>	<b>Weldability data</b> .....	13
<b>7.5</b>	<b>Internal soundness and non-destructive testing</b> .....	13
<b>7.6</b>	<b>Surface quality</b> .....	13
<b>7.7</b>	<b>Dimensions, tolerances, mass</b> .....	14
<b>7.7.1</b>	<b>Dimensions and tolerances on dimensions and shape</b> .....	14
<b>7.7.2</b>	<b>Mass of steel</b> .....	14
<b>8</b>	<b>Inspection</b> .....	14
<b>8.1</b>	<b>General</b> .....	14
<b>8.2</b>	<b>Types of inspection documents</b> .....	14
<b>8.3</b>	<b>Summary of inspections</b> .....	15
<b>8.4</b>	<b>Intermediary supply</b> .....	15

<b>9</b>	<b>Frequency of testing and preparation of samples and test pieces</b> .....	<b>15</b>
<b>9.1</b>	<b>Frequency of test</b> .....	<b>15</b>
<b>9.1.1</b>	<b>Chemical analysis</b> .....	<b>15</b>
<b>9.1.2</b>	<b>Tensile test</b> .....	<b>15</b>
<b>9.1.3</b>	<b>Impact test</b> .....	<b>16</b>
<b>9.2</b>	<b>Selection and preparation of samples for product analysis</b> .....	<b>16</b>
<b>9.3</b>	<b>Location of samples and orientation of tensile test pieces</b> .....	<b>16</b>
<b>9.4</b>	<b>Location of samples and orientation of impact test pieces</b> .....	<b>16</b>
<b>9.5</b>	<b>Preparation of test pieces for mechanical tests</b> .....	<b>16</b>
<b>9.5.1</b>	<b>General</b> .....	<b>16</b>
<b>9.5.2</b>	<b>Preparation of tensile test pieces</b> .....	<b>16</b>
<b>9.5.3</b>	<b>Preparation of impact test pieces</b> .....	<b>16</b>
<b>10</b>	<b>Test methods</b> .....	<b>17</b>
<b>10.1</b>	<b>Chemical analysis</b> .....	<b>17</b>
<b>10.2</b>	<b>Mechanical tests</b> .....	<b>17</b>
<b>10.2.1</b>	<b>Test temperatures</b> .....	<b>17</b>
<b>10.2.2</b>	<b>Tensile test</b> .....	<b>17</b>
<b>10.2.3</b>	<b>Impact test</b> .....	<b>18</b>
<b>10.3</b>	<b>Visual inspection and dimensional check</b> .....	<b>18</b>
<b>10.4</b>	<b>Non-destructive tests</b> .....	<b>18</b>
<b>10.4.1</b>	<b>General</b> .....	<b>18</b>
<b>10.4.2</b>	<b>NDT for plates</b> .....	<b>18</b>
<b>10.5</b>	<b>Retests, sorting and reprocessing</b> .....	<b>19</b>
<b>11</b>	<b>Marking - Die stamping and paint marking</b> .....	<b>19</b>
<b>12</b>	<b>Options</b> .....	<b>19</b>
<b>Annex A</b>	<b>(normative when Option 1 is specified by the purchaser) Further details of steel manufacturing procedures to be supplied by the manufacturer</b> .....	<b>34</b>
<b>Annex B</b>	<b>(normative when Option 17 is specified by the purchaser) Weldability testing and mechanical testing of butt welds</b> .....	<b>35</b>
<b>Annex C</b>	<b>(normative when Option 17 is specified by the purchaser) Weldability testing - Bead-on-plate</b> .....	<b>48</b>
<b>Annex D</b>	<b>(normative when Option 17 is specified by the purchaser) Weldability testing - Controlled thermal severity tests (CTS)</b> .....	<b>51</b>
<b>Annex E</b>	<b>(normative when Option 15 is specified by the purchaser) Cold forming characteristics for steel plates</b> .....	<b>58</b>
<b>Annex F</b>	<b>(informative) Prequalification of steels for offshore structures operating in arctic areas</b> .....	<b>59</b>
<b>Annex G</b>	<b>(informative) List of options of EN 10225-1 to -4</b> .....	<b>60</b>
<b>Bibliography</b>	.....	<b>62</b>

## SS-EN 10225-1:2019 (E)

### European foreword

This document (EN 10225-1:2019) has been prepared by Technical Committee CEN/TC 459 “ECISS - European Committee for Iron and Steel Standardization”<sup>1</sup>, the secretariat of which is held by AFNOR.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by November 2019, and conflicting national standards shall be withdrawn at the latest by November 2019.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. CEN shall not be held responsible for identifying any or all such patent rights.

This document, together with EN 10225-2:2019, EN 10225-3:2019, and EN 10225-4:2019, supersedes EN 10225:2009.

This European Standard consists of the following parts, under the general title '*Weldable structural steels for fixed offshore structures – Technical delivery conditions*':

- Part 1: Plates
- Part 2: Sections
- Part 3: Hot finished hollow sections
- Part 4: Cold formed hollow sections

In comparison to the previous edition the following technical changes were made:

- split of the standard in four parts;
- the steel names were adapted to EN 10027-1;
- former grades of group 3 are no longer listed, new options with the same enhanced properties have been introduced (**Options 2 and 3**);
- an informative Annex F was added for the prequalification of steels for fixed offshore structures in arctic areas.

According to the CEN-CENELEC Internal Regulations, the national standards organisations of the following countries are bound to implement this European Standard: Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, Former Yugoslav Republic of Macedonia, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Serbia, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and the United Kingdom.

---

<sup>1</sup> Through its subcommittee SC 3 “Structural steels other than reinforcements” (secretariat: DIN)



## 1 Scope

This document specifies requirements for weldable structural steels, in the form of plates, to be used in the fabrication of fixed offshore structures.

The following thickness limitations are given in this standard:

- S355NLO up to and including 200 mm;
- S355MLO, S420MLO, S460MLO, S500MLO up to and including 120 mm;
- S420QLO, S460QLO, S500QLO, S550QLO, S620QLO, S690QLO up to and including 150 mm.

Greater thicknesses can be agreed, provided the technical requirements of this European Standard are maintained.

This European Standard is applicable to steels for offshore structures, designed to operate in the offshore sector, including plate for structural hollow sections (see EN 10225-4). It does not apply to plates supplied for the fabrication of subsea pipelines, risers, process equipment, process piping and other utilities. It is primarily applicable to the North Sea Sector, but may also be applicable in other areas provided that due consideration is given to local conditions e.g. design temperature.

NOTE This document has an informative Annex F on the prequalification of steels for fixed offshore structures in arctic areas.

Minimum yield strengths up to 690 MPa are specified together with impact properties at temperatures down to  $-40\text{ }^{\circ}\text{C}$ .

## 2 Normative references

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

EN 1011-1, *Welding — Recommendations for welding of metallic materials — Part 1: General guidance for arc welding*

EN 10020, *Definition and classification of grades of steel*

EN 10021, *General technical delivery conditions for steel products*

EN 10027-1, *Designation systems for steels — Part 1: Steel names*

EN 10027-2, *Designation systems for steels — Part 2: Numerical system*

EN 10029, *Hot-rolled steel plates 3 mm thick or above — Tolerances on dimensions and shape*

EN 10051, *Continuously hot-rolled strip and plate/sheet cut from wide strip of non-alloy and alloy steels — Tolerances on dimensions and shape*

EN 10079, *Definition of steel products*

EN 10160, *Ultrasonic testing of steel flat product of thickness equal or greater than 6 mm (reflection method)*

## **SS-EN 10225-1:2019 (E)**

EN 10163-1, *Delivery requirements for surface condition of hot-rolled steel plates, wide flats and sections — Part 1: General requirements*

EN 10163-2, *Delivery requirements for surface condition of hot-rolled steel plates, wide flats and sections — Part 2: Plate and wide flats*

EN 10164, *Steel products with improved deformation properties perpendicular to the surface of the product — Technical delivery conditions*

EN 10168, *Steel products — Inspection documents — List of information and description*

EN 10204, *Metallic products — Types of inspection documents*

CEN/TR 10261, *Iron and steel — European standards for the determination of chemical composition*

EN ISO 148-1, *Metallic materials — Charpy pendulum impact test — Part 1: Test method (ISO 148-1)*

EN ISO 377, *Steel and steel products — Location and preparation of samples and test pieces for mechanical testing (ISO 377)*

EN ISO 643, *Steels — Micrographic determination of the apparent grain size (ISO 643)*

EN ISO 2566-1, *Steel — Conversion of elongation values — Part 1: Carbon and low alloy steels (ISO 2566-1)*

EN ISO 3452-1, *Non-destructive testing — Penetrant testing — Part 1: General principles (ISO 3452-1)*

EN ISO 4063, *Welding and allied processes — Nomenclature of processes and reference numbers (ISO 4063)*

EN ISO 4136, *Destructive tests on welds in metallic materials — Transverse tensile test (ISO 4136)*

EN ISO 4885, *Ferrous materials — Heat treatments — Vocabulary (ISO 4885)*

EN ISO 6507-1, *Metallic materials — Vickers hardness test — Part 1: Test method (ISO 6507-1)*

EN ISO 6892-1, *Metallic materials — Tensile testing — Part 1: Method of test at room temperature (ISO 6892-1)*

EN ISO 6947, *Welding and allied processes — Welding positions (ISO 6947)*

EN ISO 9712, *Non-destructive testing — Qualification and certification of NDT personnel (ISO 9712)*

EN ISO 9934-1, *Non-destructive testing — Magnetic particle testing — Part 1: General principles (ISO 9934-1)*

EN ISO 14284, *Steel and iron — Sampling and preparation of samples for the determination of chemical composition (ISO 14284)*

EN ISO 15614-1, *Specification and qualification of welding procedures for metallic materials — Welding procedure test — Part 1: Arc and gas welding of steels and arc welding of nickel and nickel alloys (ISO 15614-1)*

ISO 11484, *Steel products — Employer's qualification system for non-destructive testing (NDT) personnel*

ISO 12135, *Metallic materials — Unified method of test for the determination of quasistatic fracture toughness*

ISO 15653, *Metallic materials — Method of test for the determination of quasistatic fracture toughness of welds*

### 3 Terms and definitions

For the purposes of this document, the terms and definitions given in EN 10020, EN 10021, EN ISO 4885, EN 10079 and EN ISO 14284 and the following apply.

ISO and IEC maintain terminological databases for use in standardization at the following addresses:

- IEC Electropedia: available at <http://www.electropedia.org/>
- ISO Online browsing platform: available at <http://www.iso.org/obp>

#### 3.1

##### **continuous casting process route (concast)**

steel produced by a continuous casting process route

#### 3.2

##### **fine grain steel**

steels with fine grain structure with an equivalent index of ferritic grain size  $\geq 6$  for steel grades with ferritic/perlitic microstructure or with an equivalent index of former austenitic grain size  $\geq 5$  for steel grades with martensitic/bainitic microstructure

Note 1 to entry: For the determination of grain sizes see EN ISO 643.

#### 3.3

##### **intermediary**

organization that is supplied with products by the manufacturers and that then, in turn, supplies them without further processing or after processing without changing the properties specified in the purchase order and referenced product specification

#### 3.4

##### **manufacturer**

organization that manufactures the respective products according to the requirements of the order and to the properties specified in the referenced product specification to the final customer

#### 3.5

##### **normalized rolled**

rolling process in which the final deformation is carried out in a certain temperature range leading to a material condition equivalent to that obtained after normalizing so that the specified values of the mechanical properties are retained even after normalizing

Note 1 to entry: In international publications for both the normalizing rolling, as well as the thermomechanical rolling, the expression “controlled rolling” may be found. However in view of the different applicability of the products a distinction of the terms is necessary.

#### 3.6

##### **normalizing**

heat treatment with the object of refining and eventually making uniform the grain size of a ferrous product and comprising heating it at a temperature slightly above  $A_3$  [ $A_1$  for hypereutectoid steels], without prolonged soaking at this temperature, followed by cooling at a suitable rate