

# SVENSK STANDARD

## SS-EN 10139:2016

Fastställt/Approved: 2016-02-22  
Publicerad/Published: 2016-02-26  
Utgåva/Edition: 2  
Språk/Language: engelska/English  
ICS: 77.140.50

---

### **Kallvalsade obelagda smala band av lågkolhaltiga stål för kallformning – Tekniska leveransbestämmelser**

### **Cold rolled uncoated low carbon steel narrow strip for cold forming – Technical delivery conditions**

This preview is downloaded from [www.sis.se](http://www.sis.se). Buy the entire standard via <https://www.sis.se/std-8018969>

# Standarder får världen att fungera

*SIS (Swedish Standards Institute) är en fristående ideell förening med medlemmar från både privat och offentlig sektor. Vi är en del av det europeiska och globala nätverk som utarbetar internationella standarder. Standarder är dokumenterad kunskap utvecklad av framstående aktörer inom industri, näringsliv och samhälle och befrämjar handel över gränser, bidrar till att processer och produkter blir säkrare samt effektiviserar din verksamhet.*

## Delta och påverka

Som medlem i SIS har du möjlighet att påverka framtida standarder inom ditt område på nationell, europeisk och global nivå. Du får samtidigt tillgång till tidig information om utvecklingen inom din bransch.

## Ta del av det färdiga arbetet

Vi erbjuder våra kunder allt som rör standarder och deras tillämpning. Hos oss kan du köpa alla publikationer du behöver – allt från enskilda standarder, tekniska rapporter och standardpaket till handböcker och onlinetjänster. Genom vår webbtjänst e-nav får du tillgång till ett lättnavigerat bibliotek där alla standarder som är aktuella för ditt företag finns tillgängliga. Standarder och handböcker är källor till kunskap. Vi säljer dem.

## Utveckla din kompetens och lyckas bättre i ditt arbete

Hos SIS kan du gå öppna eller företagsinterna utbildningar kring innehåll och tillämpning av standarder. Genom vår närhet till den internationella utvecklingen och ISO får du rätt kunskap i rätt tid, direkt från källan. Med vår kunskap om standarders möjligheter hjälper vi våra kunder att skapa verklig nytta och lönsamhet i sina verksamheter.

**Vill du veta mer om SIS eller hur standarder kan effektivisera din verksamhet är du välkommen in på [www.sis.se](http://www.sis.se) eller ta kontakt med oss på tel 08-555 523 00.**



# Standards make the world go round

*SIS (Swedish Standards Institute) is an independent non-profit organisation with members from both the private and public sectors. We are part of the European and global network that draws up international standards. Standards consist of documented knowledge developed by prominent actors within the industry, business world and society. They promote cross-border trade, they help to make processes and products safer and they streamline your organisation.*

## Take part and have influence

As a member of SIS you will have the possibility to participate in standardization activities on national, European and global level. The membership in SIS will give you the opportunity to influence future standards and gain access to early stage information about developments within your field.

## Get to know the finished work

We offer our customers everything in connection with standards and their application. You can purchase all the publications you need from us - everything from individual standards, technical reports and standard packages through to manuals and online services. Our web service e-nav gives you access to an easy-to-navigate library where all standards that are relevant to your company are available. Standards and manuals are sources of knowledge. We sell them.

## Increase understanding and improve perception

With SIS you can undergo either shared or in-house training in the content and application of standards. Thanks to our proximity to international development and ISO you receive the right knowledge at the right time, direct from the source. With our knowledge about the potential of standards, we assist our customers in creating tangible benefit and profitability in their organisations.

**If you want to know more about SIS, or how standards can streamline your organisation, please visit [www.sis.se](http://www.sis.se) or contact us on phone +46 (0)8-555 523 00**



Europastandarden EN 10139:2016 gäller som svensk standard. Detta dokument innehåller den officiella engelska versionen av EN 10139:2016.

Denna standard ersätter SS-EN 10139, utgåva 1.

The European Standard EN 10139:2016 has the status of a Swedish Standard. This document contains the official English version of EN 10139:2016.

This standard supersedes the Swedish Standard SS-EN 10139, edition 1.

© Copyright/Upphovsrätten till denna produkt tillhör SIS, Swedish Standards Institute, Stockholm, Sverige. Användningen av denna produkt regleras av slutanvändarlicensen som återfinns i denna produkt, se standardens sista sidor.

© Copyright SIS, Swedish Standards Institute, Stockholm, Sweden. All rights reserved. The use of this product is governed by the end-user licence for this product. You will find the licence in the end of this document.

*Upplysningar om sakinnehållet i standarden lämnas av SIS, Swedish Standards Institute, telefon 08-555 520 00. Standarder kan beställas hos SIS Förlag AB som även lämnar allmänna upplysningar om svensk och utländsk standard.*

*Information about the content of the standard is available from the Swedish Standards Institute (SIS), telephone +46 8 555 520 00. Standards may be ordered from SIS Förlag AB, who can also provide general information about Swedish and foreign standards.*

Denna standard är framtagen av kommittén för Konstruktionsstål, SIS/TK 142.

Har du synpunkter på innehållet i den här standarden, vill du delta i ett kommande revideringsarbete eller vara med och ta fram andra standarder inom området? Gå in på [www.sis.se](http://www.sis.se) - där hittar du mer information.



EUROPEAN STANDARD

**EN 10139**

NORME EUROPÉENNE

EUROPÄISCHE NORM

February 2016

ICS 77.140.50

Supersedes EN 10139:1997

English Version

## Cold rolled uncoated low carbon steel narrow strip for cold forming - Technical delivery conditions

Feuillards non revêtus laminés à froid en aciers à bas carbone pour formage à froid - Conditions techniques de livraison

Kaltband ohne Überzug aus weichen Stählen zum Kaltumformen - Technische Lieferbedingungen

This European Standard was approved by CEN on 13 December 2015.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the CEN-CENELEC Management Centre or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the CEN-CENELEC Management Centre has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, Former Yugoslav Republic of Macedonia, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and United Kingdom.



EUROPEAN COMMITTEE FOR STANDARDIZATION  
COMITÉ EUROPÉEN DE NORMALISATION  
EUROPÄISCHES KOMITEE FÜR NORMUNG

**CEN-CENELEC Management Centre: Avenue Marnix 17, B-1000 Brussels**

<b>Contents</b>	<b>Page</b>
European foreword.....	3
<b>1 Scope</b> .....	<b>4</b>
<b>2 Normative references</b> .....	<b>4</b>
<b>3 Terms and definitions</b> .....	<b>5</b>
<b>4 Classification and designation</b> .....	<b>5</b>
<b>5 Designation</b> .....	<b>5</b>
<b>6 Properties</b> .....	<b>6</b>
<b>6.1 Steel making process and chemical composition</b> .....	<b>6</b>
<b>6.2 Choice of properties</b> .....	<b>6</b>
<b>6.3 Mechanical and technological properties</b> .....	<b>6</b>
<b>6.4 Surface characteristics</b> .....	<b>6</b>
<b>6.4.1 General</b> .....	<b>6</b>
<b>6.4.2 Surface appearance</b> .....	<b>7</b>
<b>6.4.3 Surface finish</b> .....	<b>7</b>
<b>6.5 Stretcher strain marks</b> .....	<b>7</b>
<b>6.6 Suitability for the application of surface coating</b> .....	<b>7</b>
<b>6.7 Weldability</b> .....	<b>8</b>
<b>6.8 Dimensions, mass, permissible tolerances</b> .....	<b>8</b>
<b>7 Testing</b> .....	<b>8</b>
<b>7.1 Agreement on acceptance testing</b> .....	<b>8</b>
<b>7.2 Acceptance units and number of tests</b> .....	<b>8</b>
<b>7.3 Sampling and preparation of test pieces</b> .....	<b>9</b>
<b>7.4 Test methods to be followed</b> .....	<b>9</b>
<b>7.5 Re-tests</b> .....	<b>9</b>
<b>8 Marking</b> .....	<b>9</b>
<b>9 Oiling</b> .....	<b>9</b>
<b>10 Packing</b> .....	<b>10</b>
<b>11 Information to be supplied by the purchaser</b> .....	<b>10</b>
<b>12 Disputes</b> .....	<b>10</b>

## European foreword

This document (EN 10139:2016) has been prepared by Technical Committee ECISS/TC 109 “Coated and uncoated flat products to be used for cold forming”, the secretariat of which is held by AFNOR.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by August 2016, and conflicting national standards shall be withdrawn at the latest by August 2016.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. CEN [and/or CENELEC] shall not be held responsible for identifying any or all such patent rights.

This document supersedes EN 10139:1997.

According to the CEN-CENELEC Internal Regulations, the national standards organizations of the following countries are bound to implement this European Standard: Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, Former Yugoslav Republic of Macedonia, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and the United Kingdom.

## 1 Scope

**1.1** This European Standard applies to cold rolled narrow strip in coils and cut lengths in thicknesses up to 10 mm and of widths less than 600 mm, made from low carbon, unalloyed and alloyed steels in accordance with Table 1.

These products are suitable for cold forming. They are also suitable for surface coating. On the other hand, they are not suitable for hardening treatment followed by tempering.

**1.2** This European Standard does not cover cold rolled flat products for which a separate standard already exists, particularly the following products:

- cold rolled non-oriented electrical steel sheet and strip delivered in the fully processed state (EN 10106);
- grain-oriented electrical steel sheet and strip delivered in the fully processed state (EN 10107);
- cold rolled electrical non-alloy and alloy steel sheet and strip delivered in the semi-processed state (EN 10341);
- cold rolled narrow steel strip for heat treatment (EN 10132-1 to -4);
- cold rolled steel flat products with higher yield strength for cold forming (EN 10268);
- cold rolled low carbon steel flat products for cold forming (EN 10130);
- cold reduced blackplate in coil form for the production of tinsplate or electrolytic chromium/chromium oxide coated steel (EN 10205);
- cold rolled low carbon steel flat products for vitreous enamelling (EN 10209).

## 2 Normative references

The following documents, in whole or in part, are normatively referenced in this document and are indispensable for its application. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

EN 10020, *Definition and classification of grades of steel*

EN 10021, *General technical delivery conditions for steel products*

EN 10027-1, *Designation systems for steels - Part 1: Steel names*

EN 10027-2, *Designation systems for steels - Part 2: Numerical system*

EN 10049, *Measurement of roughness average Ra and peak count R<sub>Pc</sub> on metallic flat products*

EN 10079, *Definition of steel products*

EN 10140:2006, *Cold rolled narrow steel strip - Tolerances on dimensions and shape*

EN 10204, *Metallic products - Types of inspection documents*



EN ISO 377, *Steel and steel products - Location and preparation of samples and test pieces for mechanical testing (ISO 377:2013, Corrected version 2015-06-01)*

EN ISO 6507 (all parts), *Metallic materials — Vickers hardness test (ISO 6507)*

EN ISO 6892-1:2009, *Metallic materials - Tensile testing - Part 1: Method of test at room temperature (ISO 6892-1:2009)*

ISO 10113, *Metallic materials — Sheet and strip — Determination of plastic strain ratio*

ISO 10275, *Metallic materials — Sheet and strip — Determination of tensile strain hardening exponent*

### **3 Terms and definitions**

For the purposes of this document, the terms and definitions given in EN 10079 apply.

### **4 Classification and designation**

**4.1** This European Standard specifies the grades listed in Table 1. In the case of steel grade DC01, the deoxidation method shall be left to the manufacturer's discretion. Steel grades DC03, DC04, DC05, DC06 and DC07 shall be supplied fully killed.

**4.2** Products manufactured from these steels may be ordered and supplied in different delivery conditions (see Table 1) and with different surface characteristics (see 6.4 and Table 2).

**4.3** For the purposes of the specifications of this European Standard, the selection of steel grade, delivery condition and surface characteristics are of the responsibility of the purchaser.

NOTE 1 In case of narrow widths, strip complying with this European Standard can also be wound in layers and supplied in the form of a bobbin wound coil.

NOTE 2 After uncoiling and shearing, strip can be supplied in cut lengths.

### **5 Designation**

The symbol designation of the steel grades in this European Standard is in accordance with EN 10027-1 and the numerical designation is allocated in accordance with EN 10027-2.

The standard designation consists of the words narrow strip or cut lengths, followed in order by:

- a) reference to this European Standard, EN 10139;
- b) the symbol DC, followed by the grade designation (01, 03, 04, 05, 06 and 07);
- c) the symbol for delivery condition (see Table 1);
- d) the symbol for surface appearance (MA, MB or MC, see Table 2);
- e) the symbol for surface finish where appropriate (RN, RL, RM or RR, see 6.4.3 and Table 2).

EXAMPLE 1 Designation of cold rolled narrow strip, 1,50 mm thick, having a normal tolerance on the nominal thickness, a width of 200 mm, having a normal tolerance on the nominal width, slit edges (GK) and made from

steel grade DC04, in a lightly skin-passed condition (LC) with a smooth and uniform surface appearance (MB) and a “matt” surface finish (RM):

Narrow strip EN 10140:2006 – 1,50 × 200 – GK  
Steel EN 10139 – DC04 + LC – MB – RM

**EXAMPLE 2** Designation of cold rolled narrow strip, 2,00 mm thick, having a normal tolerance on the nominal thickness, a width of 450 mm, having a normal tolerance on the nominal width, slit edges (GK) and made from steel grade DC03, in the annealed condition (A), with a bright, metallicly clean surface appearance (MA) and a smooth surface finish (RL):

Narrow strip EN 10140:2006 – 2,00 × 450 – GK  
Steel EN 10139 – DC03 + A – MA – RL

## 6 Properties

### 6.1 Steel making process and chemical composition

**6.1.1** The steel making process shall be left to the discretion of the manufacturer.

**6.1.2** The chemical composition based on ladle analysis shall be as given in Table 1.

### 6.2 Choice of properties

The products covered by this European Standard shall comply with the specifications given in Table 1. If agreed separately, they may be supplied with a special suitability for making a particular part; in this case, a maximum percentage of processing scrap may be fixed by common agreement and acceptance tests on the basis of the mechanical properties shall not apply.

### 6.3 Mechanical and technological properties

**6.3.1** The mechanical and technological properties of the products are given in Table 1. These properties are guaranteed for the periods specified in Table 1 with effect from the date that the products are made available for delivery. The purchaser shall be informed of this date when the products are to be made available, with a warning appropriate to the guarantee of mechanical properties. Storage of grade DC01 products for more than 3 months may cause a change in the mechanical properties likely to give rise to a reduction in the suitability for forming and drawing.

**6.3.2** The usual test for checking the mechanical properties given in Table 1 is the tensile test. However, if agreed at the time of ordering, hardness values may be specified instead of tensile test properties, but not both.

**6.3.3** The tensile test values shall apply to longitudinal test pieces.

### 6.4 Surface characteristics

#### 6.4.1 General

Surface characteristics concern surface appearance and surface finish. These shall be specified by the purchaser at the time of ordering. Unless otherwise specified at the time of ordering, the products shall be supplied with a surface appearance MA and a smooth surface finish RL ( $R_a \leq 0,6 \mu\text{m}$ ).

## 6.4.2 Surface appearance

**6.4.2.1** Cold rolled flat products covered by this European Standard may be supplied with surface appearances MA, MB or MC as described in Table 2.

The required surface appearance shall be stated in the designation (see Clause 5).

**6.4.2.2** The characteristics indicated in Table 2 apply to the surface actually inspected, which is generally the outside surface of coils and the top surface of lengths. The appearance of the uninspected surface shall correspond at least to surface appearance MA.

These characteristics shall not apply to the first two inner and outer laps of coil or to lengths cut from them.

## 6.4.3 Surface finish

**6.4.3.1** The surface finish may be rough, matt, smooth or mirror finish, as given in Table 2.

Products with surface appearances MA and MB are generally supplied with a smooth surface finish (RL). If rough (RR) or matt (RM) finishes are required, the corresponding symbol shall be given in the designation (see Clause 5).

The surface appearance MC shall only be supplied with a "mirror" finish (RN).

**6.4.3.2** The different surfaces finishes are characterized by the following reference values of mean roughness  $R_a$ :

RR: rough:  $R_a \geq 1,5 \mu\text{m}$ ;

RM: matt:  $0,6 \mu\text{m} < R_a \leq 1,8 \mu\text{m}$ ;

RL: smooth:  $R_a \leq 0,6 \mu\text{m}$ ;

RN: mirror finish:  $R_a \leq 0,2 \mu\text{m}$ .

## 6.5 Stretcher strain marks

The tendency towards the formation of fractures or stretcher strain marks during forming may be eliminated for a time by light skin-passing (LC) after annealing. It is in the purchaser interest to form the products as soon as possible as the tendency to form such marks may reappear a certain time after the skin-pass.

The guarantee period of freedom from stretcher strain marks is three months for grade DC01 and six months for grades DC03, DC04 and DC05, from the agreed date when the product is available for delivery.

Products of grades DC06 and DC07 do not exhibit stretcher strain marks, whether delivered skin-passed or non-skin-passed.

## 6.6 Suitability for the application of surface coating

**6.6.1** The products covered by this European Standard are suitable for surface coatings taking into account the following requirements:

a) all the products shall be suitable for organic coating;