

SVENSK STANDARD

SS-EN 13480-2:2012/A2:2016



Fastställt/Approved: 2016-10-20
Publicerad/Published: 2016-10-20
Utgåva/Edition: 1
Språk/Language: engelska/English
ICS: 23.040.01; 23.040.09

Industriella rörledningar av metalliska material – Del 2: Material

Metallic industrial piping – Part 2: Materials

This preview is downloaded from www.sis.se. Buy the entire standard via <https://www.sis.se/std-8022961>

Europastandarden EN 13480-2:2012/A2:2016 gäller som svensk standard. Detta dokument innehåller den officiella engelska versionen av EN 13480-2:2012/A2:2016.

The European Standard EN 13480-2:2012/A2:2016 has the status of a Swedish Standard. This document contains the official English version of EN 13480-2:2012/A2:2016.

© Copyright/Upphovsrätten till denna produkt tillhör SIS, Swedish Standards Institute, Stockholm, Sverige. Användningen regleras av slutanvändarlicensen för denna produkt.

© Copyright SIS, Swedish Standards Institute, Stockholm, Sweden. All rights reserved. The use of this product is governed by the end-user licence for this product.

Upplysningar om sakinnehållet i standarden lämnas av SIS, Swedish Standards Institute, telefon 08-555 520 00. Standarder kan beställas hos SIS Förlag AB som även lämnar allmänna upplysningar om svensk och utländsk standard.

Information about the content of the standard is available from the Swedish Standards Institute (SIS), telephone +46 8 555 520 00. Standards may be ordered from SIS Förlag AB, who can also provide general information about Swedish and foreign standards.

Standarden är framtagen av kommittén för Tryckkärlsstål, SIS/TK 137.

Har du synpunkter på innehållet i den här standarden, vill du delta i ett kommande revideringsarbete eller vara med och ta fram andra standarder inom området? Gå in på www.sis.se - där hittar du mer information.

EUROPEAN STANDARD

EN 13480-2:2012/A2

NORME EUROPÉENNE

EUROPÄISCHE NORM

August 2016

ICS 23.040.01

English Version

Metallic industrial piping - Part 2: Materials

Tuyauteries industrielles métalliques - Partie 2:
Matériaux

Metallische industrielle Rohrleitungen - Teil 2:
Werkstoffe

This amendment A2 modifies the European Standard EN 13480-2:2012; it was approved by CEN on 9 January 2017.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for inclusion of this amendment into the relevant national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the CEN-CENELEC Management Centre or to any CEN member.

This amendment exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the CEN-CENELEC Management Centre has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, Former Yugoslav Republic of Macedonia, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and United Kingdom.



EUROPEAN COMMITTEE FOR STANDARDIZATION
COMITÉ EUROPÉEN DE NORMALISATION
EUROPÄISCHES KOMITEE FÜR NORMUNG

CEN-CENELEC Management Centre: Avenue Marnix 17, B-1000 Brussels

Contents	Page
European foreword.....	3
1 Modification to B.2.2.5, Lowest minimum metal temperatures for austenitic stainless steels	4

European foreword

This document (EN 13480-2:2012/A2:2016) has been prepared by Technical Committee CEN/TC 267 "Industrial piping and pipelines", the secretariat of which is held by AFNOR.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by February 2017, and conflicting national standards shall be withdrawn at the latest by February 2017.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. CEN [and/or CENELEC] shall not be held responsible for identifying any or all such patent rights.

This document has been prepared under a mandate given to CEN by the European Commission and the European Free Trade Association, and supports essential requirements of EU Directive(s).

For relationship with EU Directive(s), see informative Annex ZA, which is an integral part of EN 13480-2:2012.

This document includes the text of the amendment itself. The amended/corrected pages of EN 13480-2:2012 will be published in the new Edition 2017 of the European Standard.

According to the CEN-CENELEC Internal Regulations, the national standards organisations of the following countries are bound to implement this European Standard: Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, Former Yugoslav Republic of Macedonia, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and the United Kingdom.

1 Modification to B.2.2.5, Lowest minimum metal temperatures for austenitic stainless steels

Replace Table B.2-11 with the following table:

“Table B.2-11 — Austenitic stainless steels and their lowest minimum metal temperature T_M

Material	Material number	T_M (in °C)
X1NiCrMoCu 31-27-4	1.4563	- 273
X1CrNiMoN 25-22-2	1.4466	
X1CrNi 25-21	1.4335	
X2CrNiMoN 17-13-3	1.4429	
X2CrNiMoN 17-11-2	1.4406	
X2CrNiMoN 18-12-4	1.4434	
X2CrNiMo 18-15-4	1.4438	
X2CrNiN 18-10	1.4311	
X2CrNiMo 18-14-3	1.4435	
X2CrNi 19-11	1.4306	
X2CrNiMo 17-12-2	1.4404	
X6CrNiTi 18-10	1.4541	
X6CrNiMoTi 17-12-2	1.4571	
X2CrNi 18-9	1.4307	
X1CrNiMoCuN 25-25-5	1.4537	- 196
X1NiCrMoCuN 25-20-7	1.4529	
X1CrNiMoCuN 20-18-7	1.4547	
X1NiCrMoCu 25-20-5	1.4539	
X2CrNiMoN 17-13-5	1.4439	
X3CrNiMo 17-13-3	1.4436	
X6CrNiMoNb 17-12-2	1.4580	
X2CrNiMo 17-12-3	1.4432	
X5CrNiMo 17-12-2	1.4401	
X6CrNiNb 18-10	1.4550	
X5CrNi 18-10	1.4301	
GX5CrNi9-10	1.4308	
GX5CrNiMo19-11-2	1.4408	
GX2NiCrMo28-20-2	1.4458	
GX2CrNi19-11	1.4309	
GX2CrNiMo19-11-2	1.4409	

”.