

SVENSK STANDARD

SS-EN ISO 14713-1:2017

Fastställt/Approved: 2017-06-19
Publicerad/Published: 2017-07-18
Utgåva/Edition: 2
Språk/Language: engelska/English
ICS: 25.220.40; 91.080.10

Oorganiska ytbeläggningar – Zinkbeläggningar – Rekommendationer för korrosionsskydd av järn och stål i konstruktioner – Del 1: Allmänna grunder för utformning och korrosionskydd (ISO 14713-1:2017)

Zinc coatings – Guidelines and recommendations for the protection against corrosion of iron and steel in structures – Part 1: General principles of design and corrosion resistance (ISO 14713-1:2017)

This preview is downloaded from www.sis.se. Buy the entire standard via <https://www.sis.se/std-8026930>

Standarder får världen att fungera

SIS (Swedish Standards Institute) är en fristående ideell förening med medlemmar från både privat och offentlig sektor. Vi är en del av det europeiska och globala nätverk som utarbetar internationella standarder. Standarder är dokumenterad kunskap utvecklad av framstående aktörer inom industri, näringsliv och samhälle och befrämjar handel över gränser, bidrar till att processer och produkter blir säkrare samt effektiviserar din verksamhet.

Delta och påverka

Som medlem i SIS har du möjlighet att påverka framtida standarder inom ditt område på nationell, europeisk och global nivå. Du får samtidigt tillgång till tidig information om utvecklingen inom din bransch.

Ta del av det färdiga arbetet

Vi erbjuder våra kunder allt som rör standarder och deras tillämpning. Hos oss kan du köpa alla publikationer du behöver – allt från enskilda standarder, tekniska rapporter och standardpaket till handböcker och onlinetjänster. Genom vår webbtjänst e-nav får du tillgång till ett lättnavigerat bibliotek där alla standarder som är aktuella för ditt företag finns tillgängliga. Standarder och handböcker är källor till kunskap. Vi säljer dem.

Utveckla din kompetens och lyckas bättre i ditt arbete

Hos SIS kan du gå öppna eller företagsinterna utbildningar kring innehåll och tillämpning av standarder. Genom vår närhet till den internationella utvecklingen och ISO får du rätt kunskap i rätt tid, direkt från källan. Med vår kunskap om standarders möjligheter hjälper vi våra kunder att skapa verklig nytta och lönsamhet i sina verksamheter.

Vill du veta mer om SIS eller hur standarder kan effektivisera din verksamhet är du välkommen in på www.sis.se eller ta kontakt med oss på tel 08-555 523 00.



Standards make the world go round

SIS (Swedish Standards Institute) is an independent non-profit organisation with members from both the private and public sectors. We are part of the European and global network that draws up international standards. Standards consist of documented knowledge developed by prominent actors within the industry, business world and society. They promote cross-border trade, they help to make processes and products safer and they streamline your organisation.

Take part and have influence

As a member of SIS you will have the possibility to participate in standardization activities on national, European and global level. The membership in SIS will give you the opportunity to influence future standards and gain access to early stage information about developments within your field.

Get to know the finished work

We offer our customers everything in connection with standards and their application. You can purchase all the publications you need from us - everything from individual standards, technical reports and standard packages through to manuals and online services. Our web service e-nav gives you access to an easy-to-navigate library where all standards that are relevant to your company are available. Standards and manuals are sources of knowledge. We sell them.

Increase understanding and improve perception

With SIS you can undergo either shared or in-house training in the content and application of standards. Thanks to our proximity to international development and ISO you receive the right knowledge at the right time, direct from the source. With our knowledge about the potential of standards, we assist our customers in creating tangible benefit and profitability in their organisations.

If you want to know more about SIS, or how standards can streamline your organisation, please visit www.sis.se or contact us on phone +46 (0)8-555 523 00



Europastandarden EN ISO 14713-1:2017 gäller som svensk standard. Detta dokument innehåller den officiella engelska versionen av EN ISO 14713-1:2017.

Denna standard ersätter SS-EN ISO 14713-1:2009, utgåva 1.

The European Standard EN ISO 14713-1:2017 has the status of a Swedish Standard. This document contains the official version of EN ISO 14713-1:2017.

This standard supersedes the Swedish Standard SS-EN ISO 14713-1:2009, edition 1.

© Copyright/Upphovsrätten till denna produkt tillhör SIS, Swedish Standards Institute, Stockholm, Sverige. Användningen av denna produkt regleras av slutanvändarlicensen som återfinns i denna produkt, se standardens sista sidor.

© Copyright SIS, Swedish Standards Institute, Stockholm, Sweden. All rights reserved. The use of this product is governed by the end-user licence for this product. You will find the licence in the end of this document.

Upplysningar om sakinnehållet i standarden lämnas av SIS, Swedish Standards Institute, telefon 08-555 520 00. Standarder kan beställas hos SIS Förlag AB som även lämnar allmänna upplysningar om svensk och utländsk standard.

Information about the content of the standard is available from the Swedish Standards Institute (SIS), telephone +46 8 555 520 00. Standards may be ordered from SIS Förlag AB, who can also provide general information about Swedish and foreign standards.

Denna standard är framtagen av kommittén för Oorganiska ytbeläggningar, SIS/TK 116.

Har du synpunkter på innehållet i den här standarden, vill du delta i ett kommande revideringsarbete eller vara med och ta fram andra standarder inom området? Gå in på www.sis.se - där hittar du mer information.

EUROPEAN STANDARD

EN ISO 14713-1

NORME EUROPÉENNE

EUROPÄISCHE NORM

May 2017

ICS 25.220.40

Supersedes EN ISO 14713-1:2009

English Version

Zinc coatings - Guidelines and recommendations for the
protection against corrosion of iron and steel in structures
- Part 1: General principles of design and corrosion
resistance (ISO 14713-1:2017)

Revêtements de zinc - Lignes directrices et
recommandations pour la protection contre la
corrosion du fer et de l'acier dans les constructions -
Partie 1: Principes généraux de conception et
résistance à la corrosion (ISO 14713-1:2017)

Zinküberzüge - Leitfäden und Empfehlungen zum
Schutz von Eisen- und Stahlkonstruktionen vor
Korrosion - Teil 1: Allgemeine
Konstruktionsgrundsätze und Korrosionsbeständigkeit
(ISO 14713-1:2017)

This European Standard was approved by CEN on 3 May 2017.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the CEN-CENELEC Management Centre or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the CEN-CENELEC Management Centre has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, Former Yugoslav Republic of Macedonia, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Serbia, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and United Kingdom.



EUROPEAN COMMITTEE FOR STANDARDIZATION
COMITÉ EUROPÉEN DE NORMALISATION
EUROPÄISCHES KOMITEE FÜR NORMUNG

CEN-CENELEC Management Centre: Avenue Marnix 17, B-1000 Brussels

SS-EN ISO 14713-1:2017 (E)

Contents		Page
European foreword		iv
1	Scope	1
2	Normative references	1
3	Terms and definitions	2
4	Materials	2
4.1	Iron and steel substrates.....	2
4.2	Zinc coatings.....	3
5	Selection of zinc coating	3
6	Design requirements	3
6.1	General principles of design to avoid corrosion.....	3
6.2	Design for application of different zinc coating processes.....	4
6.3	Tubes and hollow sections.....	4
6.3.1	General.....	4
6.3.2	Corrosion protection of internal and external surfaces.....	4
6.4	Connections.....	5
6.4.1	Fastenings to be used with hot dip galvanized, sherardized or thermally sprayed coatings.....	5
6.4.2	Welding considerations related to coatings.....	5
6.4.3	Brazing or soldering.....	6
6.5	Duplex systems.....	6
6.6	Maintenance.....	6
7	Corrosion in different environments	6
7.1	Atmospheric exposure.....	6
7.2	Exposure to soils.....	9
7.3	Exposure to water.....	12
7.4	Abrasion.....	12
7.5	Exposure to chemicals.....	12
7.6	Elevated temperatures.....	13
7.7	Contact with concrete.....	13
7.8	Contact with wood.....	14
7.9	Bimetallic contact.....	14
8	Accelerated test methods applied to zinc coatings	16
Bibliography		17

European foreword

This document (EN ISO 14713-1:2017) has been prepared by Technical Committee ISO/TC 107 “Metallic and other inorganic coatings” in collaboration with Technical Committee CEN/TC 262 “Metallic and other inorganic coatings, including for corrosion protection and corrosion testing of metals and alloys” the secretariat of which is held by BSI.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by November 2017, and conflicting national standards shall be withdrawn at the latest by November 2017.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. CEN [and/or CENELEC] shall not be held responsible for identifying any or all such patent rights.

This document supersedes EN ISO 14713-1:2009.

According to the CEN-CENELEC Internal Regulations, the national standards organizations of the following countries are bound to implement this European Standard: Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, Former Yugoslav Republic of Macedonia, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Serbia, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and the United Kingdom.

Endorsement notice

The text of ISO 14713-1:2017 has been approved by CEN as EN ISO 14713-1:2017 without any modification.

Zinc coatings — Guidelines and recommendations for the protection against corrosion of iron and steel in structures —

Part 1: General principles of design and corrosion resistance

1 Scope

This document provides guidelines and recommendations regarding the general principles of design which are appropriate for articles to be zinc coated for corrosion protection and the level of corrosion resistance provided by zinc coatings applied to iron or steel articles, exposed to a variety of environments. Initial protection is covered in relation to

- available standard processes,
- design considerations, and
- environments for use.

This document applies to zinc coatings applied by the following processes:

- a) hot dip galvanized coatings (applied after fabrication);
- b) hot dip galvanized coatings (applied onto continuous sheet);
- c) sherardized coatings;
- d) thermal sprayed coatings;
- e) mechanically plated coatings;
- f) electrodeposited coatings.

These guidelines and recommendations do not deal with the maintenance of corrosion protection in service for steel with zinc coatings. Guidance on this subject can be found in ISO 12944-5 and ISO 12944-8.

NOTE There are a variety of product-related standards (e.g. for nails, fasteners, ductile iron pipes, etc.) which provide specific requirements for the applied zinc coating systems which go beyond any general guidance presented in this document. These specific product-related requirements will take precedence over these general recommendations.

2 Normative references

ISO 1461, *Hot dip galvanized coatings on fabricated iron and steel articles — Specifications and test methods*

ISO 2063, *Thermal spraying — Metallic and other inorganic coatings — Zinc, aluminium and their alloys*

ISO 2064, *Metallic and other inorganic coatings — Definitions and conventions concerning the measurement of thickness*

ISO 8044:2015, *Corrosion of metals and alloys — Basic terms and definitions*

ISO 12683, *Mechanically deposited coatings of zinc — Specification and test methods*

SS-EN ISO 14713-1:2017 (E)

ISO 17668, *Zinc diffusion coatings on ferrous products — Sherardizing — Specification*

3 Terms and definitions

For the purposes of this document, the terms and definitions given in ISO 1461, ISO 2063, ISO 2064, ISO 8044, ISO 12683 and ISO 17668 and the following apply.

ISO and IEC maintain terminological databases for use in standardization at the following addresses:

- IEC Electropedia: available at <http://www.electropedia.org/>
- ISO Online browsing platform: available at <http://www.iso.org/obp>

3.1 atmospheric corrosion

corrosion with the earth's atmosphere at ambient temperature as the corrosive environment

[SOURCE: ISO 8044:2015, 3.4]

3.2 elevated temperatures

temperatures between +60 °C and +200 °C

3.3 exceptional exposure

special cases such as exposure that substantially intensifies the corrosive exposure and/or places increased demands on the corrosion protection system

3.4 life to first maintenance

time interval that can elapse after initial coating before coating deterioration reaches the point when maintenance is necessary to restore protection of the basis metal

4 Materials

4.1 Iron and steel substrates

In hot dip galvanizing, the reactivity of the steel is modified by its chemical composition, particularly by the silicon plus phosphorus contents (see ISO 14713-2). The metallurgical and chemical nature of the steel is irrelevant to protection by thermally sprayed or sherardized coatings.

The broad range of steels likely to be subject to zinc coating will commonly fall into the following categories:

- carbon steel, composed simply of iron and carbon, accounts for 90 % of steel production [e.g. EN 10025-2 and EN 10080 (steel reinforcement)];
- high-strength, low-alloy (HSLA) steels have small additions (usually <2 % by weight) of other elements, typically 1,5 % manganese, to provide additional strength for a modest price increase (e.g. EN 10025-6);
- low-alloy steel is alloyed with other elements, usually molybdenum, manganese, chromium, or nickel, in amounts of up to 10 % by weight to improve the hardenability of thick sections (e.g. EN 10083-1).

Steel can be hot rolled or cold formed. Hot rolling is used to produce angle, "I", "H" and other structural sections. Some structural sections, e.g. safety barriers, cladding rails and cladding panels, are cold formed.

Cast and wrought irons are of various metallurgical and chemical compositions. This is irrelevant to protection by thermally sprayed or sherardized coatings but special consideration is needed regarding the cast irons most suitable for hot dip galvanizing (see ISO 14713-2).

4.2 Zinc coatings

The application of zinc coatings provides an effective method of retarding or preventing corrosion of ferrous materials (see [Clause 1](#) for the range of zinc coatings/processes covered by this document). Zinc coatings are used in this regard because they protect iron and steel both by barrier action and by galvanic action.

5 Selection of zinc coating

The zinc coating system to be used should be selected by taking the following items into account:

- a) the general environment (macro-climate) in which it is to be applied;
- b) local variations in the environment (micro-climate), including anticipated future changes and any exceptional exposure;
- c) the required life to first maintenance of the zinc coating system;
- d) the need for ancillary components;
- e) the need for post-treatment for temporary protection;
- f) the need for painting, either initially (duplex system) or when the zinc coating is approaching the end of its life to first maintenance to achieve minimal maintenance cost;
- g) the availability and cost;
- h) if the life to first maintenance of the system is less than that required for the structure, its ease of maintenance.

NOTE The life for a zinc coating in any particular atmospheric exposure condition is approximately proportional to the thickness of the coating.

The operational sequence for applying the selected system should be determined in consultation with the steel fabricator and the applier of the zinc coating system.

6 Design requirements

6.1 General principles of design to avoid corrosion

Design of structures and products should influence the choice of protective system. It may be appropriate and economic to modify the design to suit the preferred protective system.

The items in a) to j) should be considered.

- a) Safe and easy access for cleaning and maintenance should be provided.
- b) Pockets and recesses in which water and dirt can collect should be avoided; a design with smooth contours facilitates application of a protective coating and helps to improve corrosion resistance. Corrosive chemicals should be directed away from structural components, e.g. drainage tubes should be used to control de-icing salts.
- c) Areas which are inaccessible after erection should be given a coating system designed to last the required life of the structure.
- d) If bimetallic corrosion (corrosion due to contact between dissimilar materials: metals and/or alloys) is possible, additional protective measures should be considered (see ISO 14713-2).
- e) Where the coated iron and steel are likely to be in contact with other building materials, special consideration should be given to the contact area; e.g. the use of paint, tapes or plastic foils should be considered.