

SVENSK STANDARD

SS-EN 10028-2:2017



Fastställt/Approved: 2017-08-02
Publicerad/Published: 2017-08-03
Utgåva/Edition: 4
Språk/Language: engelska/English
ICS: 77.140.30; 77.140.50

Platta produkter av stål för tryckändamål – Del 2: Olegerade och legerade stål med fordrade egenskaper vid förhöjd temperatur

Flat products made of steels for pressure purposes – Part 2: Non-alloy and alloy steels with specified elevated temperature properties

This preview is downloaded from www.sis.se. Buy the entire standard via <https://www.sis.se/std-8027820>

Standarder får världen att fungera

SIS (Swedish Standards Institute) är en fristående ideell förening med medlemmar från både privat och offentlig sektor. Vi är en del av det europeiska och globala nätverk som utarbetar internationella standarder. Standarder är dokumenterad kunskap utvecklad av framstående aktörer inom industri, näringsliv och samhälle och befrämjar handel över gränser, bidrar till att processer och produkter blir säkrare samt effektiviserar din verksamhet.

Delta och påverka

Som medlem i SIS har du möjlighet att påverka framtida standarder inom ditt område på nationell, europeisk och global nivå. Du får samtidigt tillgång till tidig information om utvecklingen inom din bransch.

Ta del av det färdiga arbetet

Vi erbjuder våra kunder allt som rör standarder och deras tillämpning. Hos oss kan du köpa alla publikationer du behöver – allt från enskilda standarder, tekniska rapporter och standardpaket till handböcker och onlinetjänster. Genom vår webbtjänst e-nav får du tillgång till ett lättnavigerat bibliotek där alla standarder som är aktuella för ditt företag finns tillgängliga. Standarder och handböcker är källor till kunskap. Vi säljer dem.

Utveckla din kompetens och lyckas bättre i ditt arbete

Hos SIS kan du gå öppna eller företagsinterna utbildningar kring innehåll och tillämpning av standarder. Genom vår närhet till den internationella utvecklingen och ISO får du rätt kunskap i rätt tid, direkt från källan. Med vår kunskap om standarders möjligheter hjälper vi våra kunder att skapa verklig nytta och lönsamhet i sina verksamheter.

Vill du veta mer om SIS eller hur standarder kan effektivisera din verksamhet är du välkommen in på www.sis.se eller ta kontakt med oss på tel 08-555 523 00.



Standards make the world go round

SIS (Swedish Standards Institute) is an independent non-profit organisation with members from both the private and public sectors. We are part of the European and global network that draws up international standards. Standards consist of documented knowledge developed by prominent actors within the industry, business world and society. They promote cross-border trade, they help to make processes and products safer and they streamline your organisation.

Take part and have influence

As a member of SIS you will have the possibility to participate in standardization activities on national, European and global level. The membership in SIS will give you the opportunity to influence future standards and gain access to early stage information about developments within your field.

Get to know the finished work

We offer our customers everything in connection with standards and their application. You can purchase all the publications you need from us - everything from individual standards, technical reports and standard packages through to manuals and online services. Our web service e-nav gives you access to an easy-to-navigate library where all standards that are relevant to your company are available. Standards and manuals are sources of knowledge. We sell them.

Increase understanding and improve perception

With SIS you can undergo either shared or in-house training in the content and application of standards. Thanks to our proximity to international development and ISO you receive the right knowledge at the right time, direct from the source. With our knowledge about the potential of standards, we assist our customers in creating tangible benefit and profitability in their organisations.

If you want to know more about SIS, or how standards can streamline your organisation, please visit www.sis.se or contact us on phone +46 (0)8-555 523 00



Europastandarden EN 10028-2:2017 gäller som svensk standard. Detta dokument innehåller den officiella engelska versionen av EN 10028-2:2017.

Denna standard ersätter SS-EN 10028-2:2009, utgåva 3.

The European Standard EN 10028-2:2017 has the status of a Swedish Standard. This document contains the official version of EN 10028-2:2017.

This standard supersedes the Swedish Standard SS-EN 10028-2:2009, edition 3.

© Copyright/Upphovsrätten till denna produkt tillhör SIS, Swedish Standards Institute, Stockholm, Sverige. Användningen av denna produkt regleras av slutanvändarlicensen som återfinns i denna produkt, se standardens sista sidor.

© Copyright SIS, Swedish Standards Institute, Stockholm, Sweden. All rights reserved. The use of this product is governed by the end-user licence for this product. You will find the licence in the end of this document.

Uppllysningar om sakinnehållet i standarden lämnas av SIS, Swedish Standards Institute, telefon 08-555 520 00. Standarder kan beställas hos SIS Förlag AB som även lämnar allmänna uppllysningar om svensk och utländsk standard.

Information about the content of the standard is available from the Swedish Standards Institute (SIS), telephone +46 8 555 520 00. Standards may be ordered from SIS Förlag AB, who can also provide general information about Swedish and foreign standards.

Denna standard är framtagen av kommittén för Tryckkärlsstål, SIS/TK 137.

Har du synpunkter på innehållet i den här standarden, vill du delta i ett kommande revideringsarbete eller vara med och ta fram andra standarder inom området? Gå in på www.sis.se - där hittar du mer information.

EUROPEAN STANDARD

EN 10028-2

NORME EUROPÉENNE

EUROPÄISCHE NORM

July 2017

ICS 77.140.30; 77.140.50

Supersedes EN 10028-2:2009

English Version

Flat products made of steels for pressure purposes - Part 2: Non-alloy and alloy steels with specified elevated temperature properties

Produits plats en aciers pour appareils à pression -
Partie 2 : Aciers non alliés et alliés avec
caractéristiques spécifiées à température élevée

Flacherzeugnisse aus Druckbehälterstählen - Teil 2:
Unlegierte und legierte Stähle mit festgelegten
Eigenschaften bei erhöhten Temperaturen

This European Standard was approved by CEN on 7 May 2017.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the CEN-CENELEC Management Centre or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the CEN-CENELEC Management Centre has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, Former Yugoslav Republic of Macedonia, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Serbia, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and United Kingdom.



EUROPEAN COMMITTEE FOR STANDARDIZATION
COMITÉ EUROPÉEN DE NORMALISATION
EUROPÄISCHES KOMITEE FÜR NORMUNG

CEN-CENELEC Management Centre: Avenue Marnix 17, B-1000 Brussels

SS-EN 10028-2:2017 (E)

Contents	Page
European foreword	3
1 Scope	4
2 Normative references	4
3 Terms and definitions	4
4 Tolerances on dimensions	4
5 Calculation of mass	4
6 Classification and designation	4
6.1 Classification	4
6.2 Designation	4
7 Information to be supplied by the purchaser	5
7.1 Mandatory information	5
7.2 Options	5
7.3 Example for ordering	5
8 Requirements	6
8.1 Steelmaking process	6
8.2 Delivery condition	6
8.3 Chemical composition	6
8.4 Mechanical properties	10
8.5 Surface condition	10
8.6 Internal soundness	10
8.7 Resistance to hydrogen induced cracking	10
8.8 Embrittlement of CrMo steels	10
9 Inspection	10
9.1 Types of inspection and inspection documents	10
9.2 Tests to be carried out	10
9.3 Retests, sorting and reprocessing	10
10 Sampling	10
11 Test methods	10
12 Marking	11
Annex A (informative) Guidelines for heat treatment	17
Annex B (informative) Critical time temperature parameter P_{crit} and possible combinations of stress relieving temperature and holding time	18
Annex C (informative) Reference data of strength values for 1 % (plastic) creep strain and creep rupture	20
Annex D (normative) Evaluation of resistance to hydrogen induced cracking	26
Annex E (normative) Step cooling test	27
Annex F (informative) Changes to the previous version EN 10028-2:2009	28
Annex ZA (informative) Relationship between this European Standard and the Essential Requirements of European Directive 2014/68/EU	29
Bibliography	30

European foreword

This document (EN 10028-2:2017) has been prepared by Technical Committee ECISS/TC 107 “Steels for pressure purposes”, the secretariat of which is held by DIN.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by January 2018 and conflicting national standards shall be withdrawn at the latest by January 2018.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. CEN [and/or CENELEC] shall not be held responsible for identifying any or all such patent rights.

This document supersedes EN 10028-2:2009.

This document has been prepared under a mandate given to CEN by the European Commission and the European Free Trade Association, and supports essential requirements of Directive 2014/68/EU.

For relationship with Directive 2014/68/EU, see informative Annex ZA, which is an integral part of this document.

A list of changes between this document and the previous version can be found in Annex F.

According to the CEN-CENELEC Internal Regulations, the national standards organizations of the following countries are bound to implement this European Standard: Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, Former Yugoslav Republic of Macedonia, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Serbia, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and the United Kingdom.

SS-EN 10028-2:2017 (E)

1 Scope

This European Standard specifies requirements for flat products for pressure equipment made of weldable non-alloy and alloy steels with elevated temperature properties as specified in Table 1.

The requirements and definitions of EN 10028-1:2017 also apply.

NOTE Once this European Standard is published in the EU Official Journal (OJEU) under Directive 2014/68/EU, presumption of conformity to the Essential Safety Requirements (ESRs) of Directive 2014/68/EU is limited to technical data of materials in this European Standard (Part 1 and this Part 2 of the series) and does not presume adequacy of the material to a specific item of equipment. Consequently, the assessment of the technical data stated in this material standard against the design requirements of this specific item of equipment to verify that the ESRs of Directive 2014/68/EU are satisfied, needs to be done.

2 Normative references

The following documents, in whole or in part, are normatively referenced in this document and are indispensable for its application. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

EN 1011-1:2009, *Welding - Recommendations for welding of metallic materials - Part 1: General guidance for arc welding*

EN 1011-2:2001, *Welding - Recommendations for welding of metallic materials - Part 2: Arc welding of ferritic steels*

EN 10028-1:2017, *Flat products made of steels for pressure purposes - Part 1: General requirements*

EN 10204:2004, *Metallic products - Types of inspection documents*

EN 10229:1998, *Evaluation of resistance of steel products to hydrogen induced cracking (HIC)*

3 Terms and definitions

For the purposes of this document, the terms and definitions given in EN 10028-1:2017 apply.

4 Tolerances on dimensions

See EN 10028-1:2017.

5 Calculation of mass

See EN 10028-1:2017.

6 Classification and designation

6.1 Classification

In accordance with EN 10020, the grades P235GH, P265GH, P295GH and P355GH are non-alloy quality steels. All other grades are alloy special steels.

6.2 Designation

See EN 10028-1:2017.

7 Information to be supplied by the purchaser

7.1 Mandatory information

See EN 10028-1:2017.

7.2 Options

A number of options are specified in this document and listed below. Additionally the relevant options of EN 10028-1:2017 apply. If the purchaser does not indicate a wish to implement any of these options at the time of enquiry and order, the products shall be supplied in accordance with the basic specification (see also EN 10028-1:2017).

- 1) limitation of copper and/or tin content (see Table 1, footnote b);
- 2) minimum chromium content of 0,80 % (see Table 1, footnote f);
- 3) maximum carbon content of 0,17 % for nominal thicknesses greater than 150 mm (see Table 1, footnote g);
- 4) tests in the simulated normalized condition (see 8.2.2);
- 5) delivery conditions deviating from those specified in Table 3 (see 8.2.2 and 8.2.3);
- 6) maximum carbon equivalent value for P235GH, P265GH, P295GH and P355GH (see 8.3.3);
- 7) specification of a minimum impact energy of 40 J (see Table 3);
- 8) no option, intentionally left blank;
- 9) specification of the delivery condition +QT where the usual delivery condition is +NT (see Table 3, footnote b and Table 4, footnote b);
- 10) additional impact energy values (see Table 3, footnote e);
- 11) no option, intentionally left blank;
- 12) HIC test in accordance with EN 10229 (see 8.7);
- 13) step cooling test in accordance with Annex E (see 8.8);
- 14) mid thickness test pieces for the impact test (see Clause 10).

7.3 Example for ordering

10 plates with nominal dimensions, thickness = 50 mm, width = 2 000 mm, length = 10 000 mm, made of a steel grade with the name 16Mo3 and the number 1.5415 as specified in EN 10028-2, inspection certificate 3.1 as specified in EN 10204:

10 plates – 50 × 2 000 × 10 000 – EN 10028-2 – 16Mo3 – Inspection certificate 3.1

or

10 plates – 50 × 2 000 × 10 000 – EN 10028-2 – 1.5415 – Inspection certificate 3.1

SS-EN 10028-2:2017 (E)

8 Requirements

8.1 Steelmaking process

See EN 10028-1:2017.

8.2 Delivery condition

8.2.1 Unless otherwise agreed at the time of enquiry and order, the products covered by this document shall be supplied in the usual conditions given in Table 3 (see 8.2.3).

8.2.2 Normalizing may, at the discretion of manufacturer, be replaced with normalizing rolling for the steel grades P235GH, P265GH, P295GH, P355GH and 16Mo3. In this case, additional tests in the simulated normalized condition with an agreed frequency of testing may be agreed at the time of enquiry and order to verify that the specified properties are complied with.

8.2.3 If so agreed at the time of enquiry and order, products made of steel grades P235GH, P265GH, P295GH, P355GH and 16Mo3 may also be delivered in the untreated condition. Products made of one of the other alloy grades may be supplied in the tempered or normalized condition or, in exceptional cases, in the untreated condition if so agreed (Annex A contains heat treatment information for the purchaser).

In these cases, testing shall be carried out on test pieces in the usual delivery condition as indicated in Table 3.

8.2.4 Information on welding are given in Annex B of this standard.

8.3 Chemical composition

8.3.1 The requirements of Table 1 shall apply for the chemical composition according to the cast analysis.

8.3.2 The product analysis shall not deviate from the specified values for the cast analysis as specified in Table 1 by more than the values given in Table 2.

8.3.3 A maximum value for the carbon equivalent may be agreed at time of enquiry and order for steel grades P235GH, P265GH, P295GH and P355GH. In this case, the following formula shall apply for calculation of the carbon equivalent value (CEV):

$$CEV = C + \frac{Mn}{6} + \frac{Cr + Mo + V}{5} + \frac{Ni + Cu}{15}$$

Table 1 — Chemical composition (cast analysis) ^a

Steel designation		% by mass														
Steel name	Steel number	C	Si	Mn	P max.	S max.	Al _{total}	N	Cr	Cu ^b	Mo	Nb	Ni	Ti max.	V	Others
P235GH	1.0345	≤ 0,16	≤ 0,35	0,60 ^c to 1,20	0,025	0,010	≥ 0,020	≤ 0,012 ^d	≤ 0,30	≤ 0,30	≤ 0,08	≤ 0,030	≤ 0,30	0,03	≤ 0,02	Cr+Cu+Mo+Ni ≤ 0,70
P265GH	1.0425	≤ 0,20	≤ 0,40	0,80 ^c to 1,40	0,025	0,010	≥ 0,020	≤ 0,012 ^d	≤ 0,30	≤ 0,30	≤ 0,08	≤ 0,030	≤ 0,30	0,03	≤ 0,02	
P295GH	1.0481	0,08 to 0,20	≤ 0,40	0,90 ^c to 1,50	0,025	0,010	≥ 0,020	≤ 0,012 ^d	≤ 0,30	≤ 0,30	≤ 0,08	≤ 0,030	≤ 0,30	0,03	≤ 0,02	
P355GH	1.0473	0,10 to 0,22	≤ 0,60	1,10 to 1,70	0,025	0,010	≥ 0,020	≤ 0,012 ^d	≤ 0,30	≤ 0,30	≤ 0,08	≤ 0,040	≤ 0,30	0,03	≤ 0,02	
16Mo3	1.5415	0,12 to 0,20	≤ 0,35	0,40 to 0,90	0,025	0,010	e	≤ 0,012	≤ 0,30	≤ 0,30	0,25 to 0,35	-	≤ 0,30	-	-	-
18MnMo4-5	1.5414	≤ 0,20	≤ 0,40	0,90 to 1,50	0,015	0,005	e	≤ 0,012	≤ 0,30	≤ 0,30	0,45 to 0,60	-	≤ 0,30	-	-	-
20MnMoNi4-5	1.6311	0,15 to 0,23	≤ 0,40	1,00 to 1,50	0,020	0,010	e	≤ 0,012	≤ 0,20	≤ 0,20	0,45 to 0,60	-	0,40 to 0,80	-	≤ 0,02	-
15NiCuMoNb5-6-4	1.6368	≤ 0,17	0,25 to 0,50	0,80 to 1,20	0,025	0,010	≥ 0,015	≤ 0,020	≤ 0,30	0,50 to 0,80	0,25 to 0,50	0,015 to 0,045	1,00 to 1,30	-	-	-
13CrMo4-5	1.7335	0,08 to 0,18	≤ 0,35	0,40 to 1,00	0,025	0,010	e	≤ 0,012	0,70 ^f to 1,15	≤ 0,30	0,40 to 0,60	-	-	-	-	-
13CrMoSi5-5	1.7336	≤ 0,17	0,50 to 0,80	0,40 to 0,65	0,015	0,005	e	≤ 0,012	1,00 to 1,50	≤ 0,30	0,45 to 0,65	-	≤ 0,30	-	-	-
10CrMo9-10	1.7380	0,08 to 0,14 ^g	≤ 0,50	0,40 to 0,80	0,020	0,010	e	≤ 0,012	2,00 to 2,50	≤ 0,30	0,90 to 1,10	-	-	-	-	-
12CrMo9-10	1.7375	0,10 to 0,15	≤ 0,30	0,30 to 0,80	0,015	0,010	e	≤ 0,012	2,00 to 2,50	≤ 0,25	0,90 to 1,10	-	≤ 0,30	-	-	-
X12CrMo5	1.7362	0,10 to 0,15	≤ 0,50	0,30 to 0,60	0,020	0,005	e	≤ 0,012	4,00 to 6,00	≤ 0,30	0,45 to 0,65	-	≤ 0,30	-	-	-