

SVENSK STANDARD

SS-EN 14617-6:2012

Fastställt/Approved: 2012-04-13
Publicerad/Published: 2012-04-19
Utgåva/Edition: 2
Språk/Language: engelska/English
ICS: 91.100.15

Konststen – Provningsmetoder – Del 6: Bestämning av beständighet mot plötslig temperaturförändring

Agglomerated stone – Test methods – Part 6: Determination of thermal shock resistance

This preview is downloaded from www.sis.se. Buy the entire standard via <https://www.sis.se/std-86022>

Standarder får världen att fungera

SIS (Swedish Standards Institute) är en fristående ideell förening med medlemmar från både privat och offentlig sektor. Vi är en del av det europeiska och globala nätverk som utarbetar internationella standarder. Standarder är dokumenterad kunskap utvecklad av framstående aktörer inom industri, näringsliv och samhälle och befrämjar handel över gränser, bidrar till att processer och produkter blir säkrare samt effektiviserar din verksamhet.

Delta och påverka

Som medlem i SIS har du möjlighet att påverka framtida standarder inom ditt område på nationell, europeisk och global nivå. Du får samtidigt tillgång till tidig information om utvecklingen inom din bransch.

Ta del av det färdiga arbetet

Vi erbjuder våra kunder allt som rör standarder och deras tillämpning. Hos oss kan du köpa alla publikationer du behöver – allt från enskilda standarder, tekniska rapporter och standardpaket till handböcker och onlinetjänster. Genom vår webbtjänst e-nav får du tillgång till ett lättnavigerat bibliotek där alla standarder som är aktuella för ditt företag finns tillgängliga. Standarder och handböcker är källor till kunskap. Vi säljer dem.

Utveckla din kompetens och lyckas bättre i ditt arbete

Hos SIS kan du gå öppna eller företagsinterna utbildningar kring innehåll och tillämpning av standarder. Genom vår närhet till den internationella utvecklingen och ISO får du rätt kunskap i rätt tid, direkt från källan. Med vår kunskap om standarders möjligheter hjälper vi våra kunder att skapa verklig nytta och lönsamhet i sina verksamheter.

Vill du veta mer om SIS eller hur standarder kan effektivisera din verksamhet är du välkommen in på www.sis.se eller ta kontakt med oss på tel 08-555 523 00.



Standards make the world go round

SIS (Swedish Standards Institute) is an independent non-profit organisation with members from both the private and public sectors. We are part of the European and global network that draws up international standards. Standards consist of documented knowledge developed by prominent actors within the industry, business world and society. They promote cross-border trade, they help to make processes and products safer and they streamline your organisation.

Take part and have influence

As a member of SIS you will have the possibility to participate in standardization activities on national, European and global level. The membership in SIS will give you the opportunity to influence future standards and gain access to early stage information about developments within your field.

Get to know the finished work

We offer our customers everything in connection with standards and their application. You can purchase all the publications you need from us - everything from individual standards, technical reports and standard packages through to manuals and online services. Our web service e-nav gives you access to an easy-to-navigate library where all standards that are relevant to your company are available. Standards and manuals are sources of knowledge. We sell them.

Increase understanding and improve perception

With SIS you can undergo either shared or in-house training in the content and application of standards. Thanks to our proximity to international development and ISO you receive the right knowledge at the right time, direct from the source. With our knowledge about the potential of standards, we assist our customers in creating tangible benefit and profitability in their organisations.

If you want to know more about SIS, or how standards can streamline your organisation, please visit www.sis.se or contact us on phone +46 (0)8-555 523 00



Europastandarden EN 14617-6:2012 gäller som svensk standard. Detta dokument innehåller den officiella engelska versionen av EN 14617-6:2012.

Denna standard ersätter SS-EN 14617-6:2005, utgåva 1.

The European Standard EN 14617-6:2012 has the status of a Swedish Standard. This document contains the official version of EN 14617-6:2012.

This standard supersedes the Swedish Standard SS-EN 14617-6:2005, edition 1.

© Copyright/Upphovsrätten till denna produkt tillhör SIS, Swedish Standards Institute, Stockholm, Sverige. Användningen av denna produkt regleras av slutanvändarlicensen som återfinns i denna produkt, se standardens sista sidor.

© Copyright SIS, Swedish Standards Institute, Stockholm, Sweden. All rights reserved. The use of this product is governed by the end-user licence for this product. You will find the licence in the end of this document.

Uppllysningar om sakinnehållet i standarden lämnas av SIS, Swedish Standards Institute, telefon 08-555 520 00. Standarder kan beställas hos SIS Förlag AB som även lämnar allmänna uppllysningar om svensk och utländsk standard.

Information about the content of the standard is available from the Swedish Standards Institute (SIS), telephone +46 8 555 520 00. Standards may be ordered from SIS Förlag AB, who can also provide general information about Swedish and foreign standards.

Denna standard är framtagen av kommittén för Natursten, SIS/TK 508.

Har du synpunkter på innehållet i den här standarden, vill du delta i ett kommande revideringsarbete eller vara med och ta fram andra standarder inom området? Gå in på www.sis.se - där hittar du mer information.

EUROPEAN STANDARD

EN 14617-6

NORME EUROPÉENNE

EUROPÄISCHE NORM

April 2012

ICS 91.100.15

Supersedes EN 14617-6:2005

English Version

Agglomerated stone - Test methods - Part 6: Determination of thermal shock resistance

Pierre agglomérée - Méthodes d'essai - Partie 6:
Détermination de la résistance au choc thermique

Künstlich hergestellter Stein - Prüfverfahren - Teil 6:
Bestimmung der Temperaturwechselbeständigkeit

This European Standard was approved by CEN on 9 March 2012.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the CEN-CENELEC Management Centre or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the CEN-CENELEC Management Centre has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and United Kingdom.



EUROPEAN COMMITTEE FOR STANDARDIZATION
COMITÉ EUROPÉEN DE NORMALISATION
EUROPÄISCHES KOMITEE FÜR NORMUNG

Management Centre: Avenue Marnix 17, B-1000 Brussels

Contents		Page
Foreword		3
1	Scope	4
2	Normative references	4
3	Symbols	4
4	Principle	4
5	Apparatus	4
6	Preparation of specimen	5
6.1	Sampling	5
6.2	Dimensions of the test specimens	5
6.3	Drying the specimens	5
7	Procedure	5
7.1	Control measurements before cycling	5
7.2	Description of the cycles	5
7.3	Control measurements after cycling	6
8	Expression of results	6
9	Test report	6
Bibliography		8

Foreword

This document (EN 14617-6:2012) has been prepared by Technical Committee CEN/TC 246 “Natural stones”, the secretariat of which is held by UNI.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by October 2012, and conflicting national standards shall be withdrawn at the latest by October 2012.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. CEN [and/or CENELEC] shall not be held responsible for identifying any or all such patent rights.

This document supersedes EN 14617-6:2005.

6.3 has been modified since the last edition of this European Standard.

This European Standard is one of a series of standards for test methods for agglomerated stones which includes the following:

EN 14617-1, *Agglomerated stone — Test methods — Part 1: Determination of apparent density and water absorption*

EN 14617-2, *Agglomerated stone — Test methods — Part 2: Determination of flexural strength (bending)*

EN 14617-4, *Agglomerated stone — Test methods — Part 4: Determination of the abrasion resistance*

EN 14617-5, *Agglomerated stone — Test methods — Part 5: Determination of freeze and thaw resistance*

EN 14617-6, *Agglomerated stone — Test methods — Part 6: Determination of thermal shock resistance*

EN 14617-8, *Agglomerated stone — Test methods — Part 8: Determination of resistance to fixing (dowel hole)*

EN 14617-9, *Agglomerated stone — Test methods — Part 9: Determination of impact resistance*

EN 14617-10, *Agglomerated stone — Test methods — Part 10: Determination of chemical resistance*

EN 14617-11, *Agglomerated stone — Test methods — Part 11: Determination of linear thermal expansion coefficient*

EN 14617-12, *Agglomerated stone — Test methods — Part 12: Determination of dimensional stability*

EN 14617-13, *Agglomerated stone — Test methods — Part 13: Determination of electrical resistivity*

EN 14617-15, *Agglomerated stone — Test methods — Part 15: Determination of compressive strength*

EN 14617-16, *Agglomerated stone — Test methods — Part 16: Determination of dimensions, geometric characteristics and surface quality of modular tiles*

According to the CEN/CENELEC Internal Regulations, the national standards organizations of the following countries are bound to implement this European Standard: Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and the United Kingdom.

SS-EN 14617-6:2012 (E)

1 Scope

This European Standard specifies a method to assess possible modifications of agglomerated stones under the effect of sudden changes in temperature (thermal shock) by immersion in hot water.

2 Normative references

The following documents, in whole or in part, are normatively referenced in this document and are indispensable for its application. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

EN 14617-2:2008, *Agglomerated stone — Test methods — Part 2: Determination of flexural strength (bending)*

3 Symbols

For the purposes of this document, the following symbols apply.

m_0 mass of the dried specimen before the test, in g;

m_f mass of the dried specimen after the test, in g;

Δm % change in the mass of the dried specimens, as a percentage;

R_f flexural strength average value of dried, reference specimens, in MPa;

R_{sf} flexural strength average value of specimens after 20 cycles, in MPa;

$\Delta R_{f,20}$ coefficient of thermal shock resistance as change_in flexural strength (as a percentage after 20 cycles).

4 Principle

After drying at (40 ± 5) °C until constant mass is attained, the specimens are subjected to successive cycles, each formed by thermal shock at (70 ± 5) °C followed by immediate immersion in water at (15 ± 5) °C. After 20 cycles, the specimens are visually inspected and compared with the reference specimen, and all visible alterations recorded. Finally, the mass and flexural strength changes of specimens after 20 cycles will be determined in comparison with the values of the same quantities of reference specimens.

NOTE The selected test temperature of 70 °C is for flooring and wall applications.

5 Apparatus

5.1 A ventilated oven capable of maintaining a temperature of (70 ± 5) °C.

5.2 A tank equipped with a cooling system capable of maintaining a temperature of (15 ± 5) °C and a flat base comprising small non-oxidising and non-absorbent supports for the specimens.

5.3 A weighing instrument with an accuracy of at least 0,01 % of the mass to be weighed.

5.4 A desiccator.