

SVENSK STANDARD

SS-ISO 22891:2013



Fastställt/Approved: 2013-03-21
Publicerad/Published: 2013-03-25
Utgåva/Edition: 1
Språk/Language: engelska/English
ICS: 85.060

**Papper – Bestämning av transmittans genom diffus
reflektansmätning (ISO 22891:2013, IDT)**

**Paper – Determination of transmittance by diffuse reflectance
measurement (ISO 22891:2013, IDT)**

This preview is downloaded from www.sis.se. Buy the entire standard via <https://www.sis.se/std-89503>

Standarder får världen att fungera

SIS (Swedish Standards Institute) är en fristående ideell förening med medlemmar från både privat och offentlig sektor. Vi är en del av det europeiska och globala nätverk som utarbetar internationella standarder. Standarder är dokumenterad kunskap utvecklad av framstående aktörer inom industri, näringsliv och samhälle och befrämjar handel över gränser, bidrar till att processer och produkter blir säkrare samt effektiviserar din verksamhet.

Delta och påverka

Som medlem i SIS har du möjlighet att påverka framtida standarder inom ditt område på nationell, europeisk och global nivå. Du får samtidigt tillgång till tidig information om utvecklingen inom din bransch.

Ta del av det färdiga arbetet

Vi erbjuder våra kunder allt som rör standarder och deras tillämpning. Hos oss kan du köpa alla publikationer du behöver – allt från enskilda standarder, tekniska rapporter och standardpaket till handböcker och onlinetjänster. Genom vår webbtjänst e-nav får du tillgång till ett lättnavigerat bibliotek där alla standarder som är aktuella för ditt företag finns tillgängliga. Standarder och handböcker är källor till kunskap. Vi säljer dem.

Utveckla din kompetens och lyckas bättre i ditt arbete

Hos SIS kan du gå öppna eller företagsinterna utbildningar kring innehåll och tillämpning av standarder. Genom vår närhet till den internationella utvecklingen och ISO får du rätt kunskap i rätt tid, direkt från källan. Med vår kunskap om standarders möjligheter hjälper vi våra kunder att skapa verklig nytta och lönsamhet i sina verksamheter.

Vill du veta mer om SIS eller hur standarder kan effektivisera din verksamhet är du välkommen in på www.sis.se eller ta kontakt med oss på tel 08-555 523 00.



Standards make the world go round

SIS (Swedish Standards Institute) is an independent non-profit organisation with members from both the private and public sectors. We are part of the European and global network that draws up international standards. Standards consist of documented knowledge developed by prominent actors within the industry, business world and society. They promote cross-border trade, they help to make processes and products safer and they streamline your organisation.

Take part and have influence

As a member of SIS you will have the possibility to participate in standardization activities on national, European and global level. The membership in SIS will give you the opportunity to influence future standards and gain access to early stage information about developments within your field.

Get to know the finished work

We offer our customers everything in connection with standards and their application. You can purchase all the publications you need from us - everything from individual standards, technical reports and standard packages through to manuals and online services. Our web service e-nav gives you access to an easy-to-navigate library where all standards that are relevant to your company are available. Standards and manuals are sources of knowledge. We sell them.

Increase understanding and improve perception

With SIS you can undergo either shared or in-house training in the content and application of standards. Thanks to our proximity to international development and ISO you receive the right knowledge at the right time, direct from the source. With our knowledge about the potential of standards, we assist our customers in creating tangible benefit and profitability in their organisations.

If you want to know more about SIS, or how standards can streamline your organisation, please visit www.sis.se or contact us on phone +46 (0)8-555 523 00



Den internationella standarden ISO 22891:2013 gäller som svensk standard. Detta dokument innehåller den officiella engelska versionen av ISO 22891:2013.

The International Standard ISO 22891:2013 has the status of a Swedish Standard. This document contains the official English version of ISO 22891:2013.

© Copyright/Upphovsrätten till denna produkt tillhör SIS, Swedish Standards Institute, Stockholm, Sverige. Användningen av denna produkt regleras av slutanvändarlicensen som återfinns i denna produkt, se standardens sista sidor.

© Copyright SIS, Swedish Standards Institute, Stockholm, Sweden. All rights reserved. The use of this product is governed by the end-user licence for this product. You will find the licence in the end of this document.

Uppllysningar om sakinnehållet i standarden lämnas av SIS, Swedish Standards Institute, telefon 08-555 520 00. Standarder kan beställas hos SIS Förlag AB som även lämnar allmänna uppllysningar om svensk och utländsk standard.

Information about the content of the standard is available from the Swedish Standards Institute (SIS), telephone +46 8 555 520 00. Standards may be ordered from SIS Förlag AB, who can also provide general information about Swedish and foreign standards.

Standarden är framtagen av kommittén för Fysikaliska provningsmetoder, SIS/TK 157/AG 1.

Har du synpunkter på innehållet i den här standarden, vill du delta i ett kommande revideringsarbete eller vara med och ta fram andra standarder inom området? Gå in på www.sis.se - där hittar du mer information.

Contents

	Page
Foreword	iv
Introduction	v
1 Scope	1
2 Normative references	1
3 Terms and definitions	1
4 Principle	3
5 Apparatus	3
6 Sampling	4
7 Preparation of test pieces	4
8 Procedure	4
9 Calculation	4
10 Test report	5
Annex A (normative) Spectral characteristics of reflectometers for measuring luminous reflectance factors	6
Annex B (informative) Relationship between transmittance and opacity	8
Annex C (informative) Precision	9
Bibliography	11

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

International Standards are drafted in accordance with the rules given in the ISO/IEC Directives, Part 2.

The main task of technical committees is to prepare International Standards. Draft International Standards adopted by the technical committees are circulated to the member bodies for voting. Publication as an International Standard requires approval by at least 75 % of the member bodies casting a vote.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights.

ISO 22891 was prepared by Technical Committee ISO/TC 6, *Paper, board and pulps*.

This second edition cancels and replaces the first edition (ISO 22891:2007), of which it constitutes a minor revision.

Introduction

This International Standard presents a method of determining the transmittance indirectly from reflectance factor data obtained by measurement under specified conditions. The equation used to calculate the transmittance is based on the Kubelka-Munk theory of light scattering and light absorption, and the equation can therefore only be strictly applied if measurements are made on materials which scatter light sufficiently to justify the application of this theory.

The reflectance factor depends on the conditions of measurement, and particularly on the spectral and geometric characteristics of the instrument used for its determination. This International Standard should therefore be read in conjunction with ISO 2469 and ISO 2471.

The transmittance value obtained by this method is a single value compatible with the opacity value determined according to ISO 2471, since all measurements are related to the luminance factor calculated with respect to the CIE illuminant C.

The method described in this International Standard gives only the total transmittance and does not distinguish between regular transmittance and diffuse transmittance. It does not provide a direct measure of the ability to distinguish, for example, written text through a transparent medium. This can be assessed only if the ratio of the regular to the diffuse transmittance is known.

It is emphasized that this method is for the determination not of the transmittance by direct measurement but of the transmittance obtained indirectly from reflectance factor measurements. Under ideal conditions, they are the same, but in practice, it can be necessary to emphasize the difference.

Paper — Determination of transmittance by diffuse reflectance measurement

1 Scope

This International Standard specifies a method for the calculation of transmittance based upon diffuse reflectance measurements.

The use of the method is restricted to white and near-white translucent papers (see 3.9). If it is necessary to determine the transmittance of papers which contain fluorescent whitening agents, the fluorescence emission is eliminated using the prescribed UV cut-off filter.

NOTE This means that, although this International Standard refers to ISO 2469, which permits the use of both filter colourimeters and abridged spectrophotometers, a filter colourimeter with no means of eliminating the emission of fluorescence is not suitable for this type of measurement if fluorescent whitening agents are present.

2 Normative references

The following referenced documents are indispensable for the application of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 186, *Paper and board — Sampling to determine average quality*

ISO 2469, *Paper, board and pulps — Measurement of diffuse radiance factor (diffuse reflectance factor)*

ASTM E308-06, *Standard Practice for Computing the Colors of Objects by Using the CIE System*

3 Terms and definitions

For the purposes of this document, the following terms and definitions apply.

3.1 reflectance factor

R

ratio of the radiation reflected by a body to that reflected by the perfect reflecting diffuser under the same conditions of illumination and detection

Note 1 to entry: This ratio is often expressed as a percentage.

3.2 luminance factor (C)

R_y

reflectance factor weighted with reference to the colour matching function $\bar{y}(\lambda)$ of the CIE 1931(2°) Standard Observer and the CIE illuminant C

Note 1 to entry: This property corresponds to the attribute of visual perception of the luminance of the reflecting surface. The strict definition refers to the luminous efficiency function (for photopic vision) $V(\lambda)$. Since this function is identical with the $\bar{y}(\lambda)$ function, the latter is preferred here, since it is more familiar in a paper technology context and it is this function which is indicated in connection with the ASTM E308 tables necessary for the computations.

Note 2 to entry: Since the concept of “luminance” in this International Standard is strictly for small fields of view, it only embodies the $\bar{y}(\lambda)$ function of the CIE 1931(2°) Standard Observer. Thus, it is sufficient to only add the qualification (C) to indicate the CIE illuminant C, and not the full designation (C/2°).

3.3
single-sheet luminance factor (C)

R_0
luminance factor (C) of a single sheet of paper over a black cavity

3.4
white backing luminance factor (C)

R_w
luminance factor (C) of a white backing

3.5
intrinsic luminance factor (C)

R_∞
luminance factor (C) of a layer or pad of material thick enough to be opaque, i.e. such that increasing the thickness of the pad by doubling the number of sheets results in no change in the measured luminance factor

3.6
transmittance

τ
ratio of the transmitted radiant or luminous flux to the incident flux under given conditions

[CIE Publication 17.4:1987, 845-04-59]

3.7
regular transmittance

τ_r
ratio of the regularly transmitted part of the (whole) transmitted flux to the incident flux

[CIE Publication 17.4:1987, 845-04-61]

3.8
diffuse transmittance

τ_d
ratio of the diffusely transmitted part of the (whole) transmitted flux to the incident flux

[CIE Publication 17.4:1987, 845-04-63]

Note 1 to entry: $\tau = \tau_r + \tau_d$.

3.9
transparent medium

medium in which the transmission is mainly regular and which usually has a high regular transmittance in the spectral range of interest

[CIE Publication 17.4:1987, 845-04-108]

Note 1 to entry: Objects may be seen distinctly through a medium, which is transparent in the visible region, if the geometric form of the medium is suitable.

3.10
translucent medium

medium which transmits visible radiation largely by diffuse transmission

[CIE Publication 17.4:1987, 845-04-109]

Note 1 to entry: Objects are not seen distinctly through a translucent medium.

3.11

transmittance from reflectance factor measurements

T

transmittance obtained by direct measurement of luminance factor (C) (filter reflectometer) or determination of luminance factor (C) from measured reflectance factors (abridged spectrophotometer) and subsequent calculation as defined in this method

4 Principle

The luminance factors of a single sheet of paper over a black cavity and over a white backing are determined by measurement according to standard procedures. The transmittance is calculated from the luminance factors.

5 Apparatus

5.1 Reflectometer, having the geometric, spectral and photometric characteristics described in ISO 2469, equipped for the measurement of the luminance factor, and calibrated in accordance with the provisions of ISO 2469.

5.2 Filter-function: in the case of a filter reflectometer, a filter that, in conjunction with the optical characteristics of the basic instrument, gives an overall response equivalent to the CIE tristimulus value Y of the CIE 1931 standard colourimetric system of the test piece evaluated for the CIE illuminant C.

In the case of an abridged spectrophotometer, a function that permits calculation of the CIE tristimulus value Y of the CIE 1931 standard colourimetric system of the test piece evaluated for the CIE illuminant C using the weighting functions given in [Annex A](#). The spectrophotometer should be fitted with a 420 nm UV cut-off filter for fluorescence elimination, as described in ISO 2469.

5.3 Reference standards, issued by an ISO/TC 6 authorized laboratory in accordance with the provisions of ISO 2469 for calibration of the instrument and the working standards. For maximum accuracy, reference standards having assigned values within the maximum range expected for the particular product to be tested should be selected.

If there is reason to suspect that the instrument has poor linearity or that the deviations from the true colour matching and observer functions are greater than can be tolerated, the use of product-specific reference standards should be considered.

Use new reference standards sufficiently frequently to ensure that the reflectometer is maintained in agreement with the reference instrument.

5.4 Two working standards, calibrated in the apparatus concerned against ISO reference standards of level 3 supplied by an authorized laboratory (see ISO 2469). Calibrate the working standards sufficiently frequently to ensure that satisfactory calibration is maintained.

5.5 Black cavity, for calibration or validation of the low end of the photometric scale, and also for use as a black backing for some of the measurements. This black cavity shall have a radiance factor which does not differ from its nominal value by more than 0,2 percentage points at all wavelengths. The black cavity should be stored upside-down in a dust-free environment or with a protective cover. During calibration, the instrument shall be adjusted to the nominal value of the black cavity.

It is not yet possible to institute a system of reference standards to enable testing laboratories to check the reflectance factor of the black cavity. At the time of delivery, the level should be guaranteed by the instrument maker. Questions concerning the use and condition of the black cavity should be resolved by contacting the instrument maker.

5.6 White backing, consisting of an opaque non-fluorescent white material with a flat, matt surface.